



## ANALYSIS REPORT BBM21-09948

To COD SGS MINERALS - GEOCHEM VANCOUVER  
PANCON RESOURCES CAROLINAS CORP – JEN SPOHN  
201 ROUTE 17 NORTH, 7TH FLOOR  
Rutherford 07070  
Bergen  
UNITED STATES

|                   |                                    |                  |                           |
|-------------------|------------------------------------|------------------|---------------------------|
| Order Number      | PANCON_RESOURCES                   | Date Received    | 27-May-2021               |
| Project           | The Brewer Gold Project            | Date Analysed    | 15-Jun-2021 - 13-Jul-2021 |
| Submission Number | *SD* Pancon/ Brewer Gold B21C-009/ | Date Completed   | 13-Jul-2021               |
| 111 Core (1-56)   |                                    | SGS Order Number | BBM21-09948               |
| Number of Samples | 56                                 |                  |                           |

### Methods Summary

| Number of Sample | Method Code | Description  |
|------------------|-------------|--|
| 56               | G_WGH_KG    | Weight of samples received                                   |
| 52               | G_PRP       | Combined Sample Preparation                                  |
| 56               | GE_FAA30V5  | Au, FAS, exploration grade, AAS, 30g-5ml                     |
| 51               | GE_DIG40Q12 | 4 Acid Digest (HCL/HCLO4/HF/HNO3)                            |
| 51               | GE_ICP40Q12 | 4 Acid Digest (HCL/HCLO4/HF/HNO3), ICP, 0.2g-12ml            |
| 51               | GE_IMS40Q12 | 4 Acid Digest Package (HCL/HCLO4/HF/HNO3), ICP-MS, 0.2g-12ml |

### Comments

Preparation of samples was performed at the SGS Sudbury site.

Analysis of samples was performed at the SGS Burnaby site.

Authorised Signatory

John Chiang  
Laboratory Operations  
Manager

This document is issued by the Company under its General Conditions of Service accessible at <https://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

**WARNING:** The sample(s) to which the findings recorded herein (the "Findings") relate was(were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativeness of any goods and strictly relate to the sample(s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes.

- not analysed | -- element not determined | I.S. insufficient sample | L.N.R. listed not received



Order Number PANCON\_RESOURCES  
 Project The Brewer Gold Project  
 Submission Number \*SD\* Pancon/ Brewer Gold B21C-  
 009/ 111 Core (1-56)  
 Number of Samples 56

## ANALYSIS REPORT BBM21-09948

| Element Method | WTG<br>G_WGH_KG | @Au<br>GE_FAA30V5 | @Al<br>GE_ICP40Q12 | @Ba<br>GE_ICP40Q12 | @Ca<br>GE_ICP40Q12 | @Cr<br>GE_ICP40Q12 |
|----------------|-----------------|-------------------|--------------------|--------------------|--------------------|--------------------|
| Lower Limit    | 0.01            | 5                 | 0.01               | 1                  | 0.01               | 1                  |
| Upper Limit    | --              | 10,000            | 15                 | 10,000             | 15                 | 10,000             |
| Unit           | kg              | ppb               | %                  | ppm m / m          | %                  | ppm m / m          |
| 1751001        | 5.05            | 164               | 0.14               | 44                 | 0.70               | 11                 |
| 1751002        | 5.60            | 219               | 0.09               | 53                 | 0.01               | 9                  |
| 1751003        | 3.50            | 88                | 0.07               | 45                 | 0.01               | 9                  |
| 1751004        | 4.62            | 143               | 0.07               | 76                 | <0.01              | 12                 |
| 1751005        | 3.87            | 185               | 0.09               | 82                 | 0.01               | 26                 |
| 1751006        | 5.76            | 365               | 0.02               | 7                  | <0.01              | 22                 |
| 1751007        | 5.74            | 417               | 0.06               | 18                 | <0.01              | 22                 |
| 1751008        | 4.59            | 530               | 0.05               | 26                 | <0.01              | 16                 |
| 1751009        | 2.60            | 125               | 0.03               | 16                 | <0.01              | 7                  |
| 1751010        | 0.05            | 1280              | -                  | -                  | -                  | -                  |
| 1751011        | 5.44            | 289               | 0.06               | 23                 | <0.01              | 20                 |
| 1751012        | 3.79            | 462               | 0.10               | 66                 | 0.01               | 18                 |
| 1751013        | 4.13            | 233               | 0.12               | 85                 | 0.02               | 22                 |
| 1751014        | 4.82            | 173               | 0.15               | 94                 | 0.02               | 21                 |
| 1751015        | 3.80            | 180               | 0.12               | 73                 | 0.02               | 16                 |
| 1751016        | 3.96            | 82                | 0.14               | 68                 | 0.02               | 11                 |
| 1751017        | 2.67            | 39                | 1.24               | 110                | 0.02               | 8                  |
| 1751018        | 2.16            | 51                | 1.41               | 196                | 0.04               | 8                  |
| 1751019        | 5.72            | 361               | 2.62               | 188                | 0.03               | 15                 |
| 1751020        | 0.06            | <5                | -                  | -                  | -                  | -                  |
| 1751021        | 3.99            | 305               | 2.62               | 78                 | 0.02               | 9                  |
| 1751022        | 4.10            | 205               | 3.17               | 84                 | 0.02               | 11                 |
| 1751023        | 3.76            | 30                | 0.66               | 79                 | <0.01              | 15                 |
| 1751024        | 5.24            | 184               | 3.36               | 166                | 0.02               | 16                 |
| 1751025        | 6.30            | 191               | 4.16               | 142                | 0.01               | 12                 |
| 1751026        | 6.15            | 153               | 4.53               | 287                | 0.03               | 11                 |
| 1751027        | 4.84            | 75                | 3.69               | 450                | 0.04               | 14                 |
| 1751028        | 5.74            | 168               | 4.11               | 295                | 0.03               | 16                 |
| 1751029        | 4.51            | 138               | 4.42               | 589                | 0.04               | 9                  |

- not analysed | -- element not determined | I.S. insufficient sample | L.N.R. listed not received



Order Number PANCON\_RESOURCES  
 Project The Brewer Gold Project  
 Submission Number \*SD\* Pancon/ Brewer Gold B21C-  
 009/ 111 Core (1-56)  
 Number of Samples 56

**ANALYSIS REPORT BBM21-09948**

| Element      | WTG      | @Au        | @Al         | @Ba         | @Ca         | @Cr         |
|--------------|----------|------------|-------------|-------------|-------------|-------------|
| Method       | G_WGH_KG | GE_FAA30V5 | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 |
| Lower Limit  | 0.01     | 5          | 0.01        | 1           | 0.01        | 1           |
| Upper Limit  | --       | 10,000     | 15          | 10,000      | 15          | 10,000      |
| Unit         | kg       | ppb        | %           | ppm m / m   | %           | ppm m / m   |
| 1751030      | -        | 150        | -           | -           | -           | -           |
| 1751031      | 4.46     | 39         | 2.05        | 141         | 0.02        | 8           |
| 1751032      | 5.47     | 168        | 4.29        | 309         | 0.03        | 12          |
| 1751033      | 6.16     | 140        | 5.42        | 309         | 0.03        | 8           |
| 1751034      | 4.32     | 19         | 1.21        | 152         | 0.03        | 12          |
| 1751035      | 5.27     | 96         | 1.47        | 213         | 0.02        | 13          |
| 1751036      | 4.09     | 173        | 1.98        | 225         | 0.03        | 15          |
| 1751037      | 5.73     | 116        | 3.41        | 119         | 0.02        | 10          |
| 1751038      | 6.26     | 125        | 3.83        | 83          | 0.01        | 9           |
| 1751039      | 5.75     | 110        | 3.75        | 197         | 0.02        | 13          |
| 1751040      | 0.05     | 322        | -           | -           | -           | -           |
| 1751041      | 5.88     | 143        | 4.45        | 194         | 0.02        | 12          |
| 1751042      | 5.99     | 79         | 6.59        | 315         | 0.03        | 10          |
| 1751043      | 5.17     | 140        | 4.93        | 229         | 0.03        | 9           |
| 1751044      | 5.84     | 57         | 6.55        | 149         | 0.03        | 7           |
| 1751045      | 6.20     | 79         | 4.87        | 129         | 0.03        | 10          |
| 1751046      | 2.62     | 28         | 1.45        | 27          | <0.01       | 8           |
| 1751047      | 5.16     | 38         | 3.60        | 31          | <0.01       | 11          |
| 1751048      | 5.42     | 72         | 4.07        | 69          | 0.02        | 13          |
| 1751049      | 5.16     | 146        | 8.13        | 273         | 0.06        | 11          |
| 1751050      | 2.03     | <5         | -           | -           | -           | -           |
| 1751051      | 6.09     | 292        | 5.94        | 71          | 0.03        | 9           |
| 1751052      | 6.44     | 1130       | 7.30        | 59          | 0.07        | 11          |
| 1751053      | 7.17     | 120        | 6.31        | 44          | 0.05        | 7           |
| 1751054      | 7.10     | 77         | 8.23        | 26          | 0.04        | 11          |
| 1751055      | 6.66     | 97         | 9.83        | 101         | 0.05        | 12          |
| 1751056      | 6.20     | 521        | 8.29        | 66          | 0.05        | 13          |
| *Dup 1751039 | -        | 111        | 3.80        | 207         | 0.02        | 12          |
| *Rep 1751027 | -        | 75         | -           | -           | -           | -           |

- not analysed | -- element not determined | I.S. insufficient sample | L.N.R. listed not received



Order Number PANCON\_RESOURCES  
 Project The Brewer Gold Project  
 Submission Number \*SD\* Pancon/ Brewer Gold B21C-  
 009/ 111 Core (1-56)  
 Number of Samples 56

## ANALYSIS REPORT BBM21-09948

| Element         | WTG      | @Au        | @Al         | @Ba         | @Ca         | @Cr         |
|-----------------|----------|------------|-------------|-------------|-------------|-------------|
| Method          | G_WGH_KG | GE_FAA30V5 | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 |
| Lower Limit     | 0.01     | 5          | 0.01        | 1           | 0.01        | 1           |
| Upper Limit     | --       | 10,000     | 15          | 10,000      | 15          | 10,000      |
| Unit            | kg       | ppb        | %           | ppm m / m   | %           | ppm m / m   |
| *Std OREAS 279  | -        | 6480       | -           | -           | -           | -           |
| *Blk BLANK      | -        | <5         | -           | -           | -           | -           |
| *Std GS-9B      | -        | 8690       | -           | -           | -           | -           |
| *Std OREAS 235  | -        | 1590       | -           | -           | -           | -           |
| *Rep 1751041    | -        | 146        | -           | -           | -           | -           |
| *Blk BLANK      | -        | <5         | -           | -           | -           | -           |
| *Rep 1751053    | -        | -          | 6.39        | 46          | 0.05        | 10          |
| *Std OREAS 905  | -        | -          | 7.34        | 2699        | 0.57        | 12          |
| *Blk BLANK      | -        | -          | <0.01       | <1          | <0.01       | <1          |
| *Blk BLANK      | -        | -          | 0.01        | <1          | <0.01       | <1          |
| *Std OREAS 601b | -        | -          | 6.33        | 853         | 0.82        | 17          |
| *Std OREAS 601b | -        | -          | 6.41        | 395         | 0.85        | 17          |
| *Std OREAS 905  | -        | -          | 7.28        | 2666        | 0.56        | 15          |
| *Blk BLANK      | -        | -          | <0.01       | <1          | <0.01       | <1          |
| *Rep 1751038    | -        | -          | 3.68        | 80          | 0.01        | 8           |

| Element     | @Cu         | @Fe         | @K          | @Li         | @Mg         | @Mn         |
|-------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Method      | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 |
| Lower Limit | 0.5         | 0.01        | 0.01        | 1           | 0.01        | 2           |
| Upper Limit | 10,000      | 15          | 15          | 10,000      | 15          | 10,000      |
| Unit        | ppm m / m   | %           | %           | ppm m / m   | %           | ppm m / m   |
| 1751001     | 126         | 1.62        | <0.01       | <1          | <0.01       | 21          |
| 1751002     | 65.5        | 1.81        | <0.01       | <1          | <0.01       | 22          |
| 1751003     | 10.3        | 0.71        | <0.01       | <1          | <0.01       | 35          |
| 1751004     | 36.3        | 1.29        | <0.01       | <1          | <0.01       | 39          |
| 1751005     | 11.7        | 1.51        | <0.01       | <1          | <0.01       | 26          |
| 1751006     | 159         | 4.03        | <0.01       | <1          | <0.01       | 51          |
| 1751007     | 47.8        | 4.61        | <0.01       | <1          | <0.01       | 25          |

- not analysed | -- element not determined | I.S. insufficient sample | L.N.R. listed not received



Order Number PANCON\_RESOURCES  
 Project The Brewer Gold Project  
 Submission Number \*SD\* Pancon/ Brewer Gold B21C-  
 009/ 111 Core (1-56)  
 Number of Samples 56

**ANALYSIS REPORT BBM21-09948**

| Element     | @Cu         | @Fe         | @K          | @Li         | @Mg         | @Mn         |
|-------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Method      | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 |
| Lower Limit | 0.5         | 0.01        | 0.01        | 1           | 0.01        | 2           |
| Upper Limit | 10,000      | 15          | 15          | 10,000      | 15          | 10,000      |
| Unit        | ppm m / m   | %           | %           | ppm m / m   | %           | ppm m / m   |
| 1751008     | 22.9        | 1.28        | <0.01       | <1          | <0.01       | 53          |
| 1751009     | 11.2        | 0.65        | <0.01       | <1          | <0.01       | 41          |
| 1751011     | 195         | 4.35        | <0.01       | <1          | <0.01       | 52          |
| 1751012     | 144         | 3.36        | <0.01       | <1          | <0.01       | 23          |
| 1751013     | 114         | 2.48        | <0.01       | <1          | <0.01       | 48          |
| 1751014     | 73.6        | 1.67        | <0.01       | <1          | <0.01       | 23          |
| 1751015     | 70.1        | 1.63        | <0.01       | <1          | <0.01       | 40          |
| 1751016     | 10.4        | 1.02        | <0.01       | <1          | <0.01       | 23          |
| 1751017     | 11.2        | 1.72        | <0.01       | <1          | <0.01       | 43          |
| 1751018     | 11.4        | 0.84        | <0.01       | <1          | <0.01       | 29          |
| 1751019     | 189         | 2.83        | 0.01        | 1           | <0.01       | 35          |
| 1751021     | 117         | 3.02        | 0.01        | 1           | <0.01       | 21          |
| 1751022     | 206         | 2.60        | <0.01       | 2           | <0.01       | 39          |
| 1751023     | 20.1        | 3.39        | <0.01       | <1          | <0.01       | 40          |
| 1751024     | 60.0        | 2.49        | 0.01        | 2           | <0.01       | 27          |
| 1751025     | 69.2        | 2.15        | 0.02        | 2           | <0.01       | 19          |
| 1751026     | 79.9        | 2.34        | 0.01        | 1           | <0.01       | 29          |
| 1751027     | 44.6        | 1.93        | 0.02        | 1           | <0.01       | 37          |
| 1751028     | 90.9        | 2.56        | 0.07        | 2           | <0.01       | 40          |
| 1751029     | 51.3        | 1.97        | 0.04        | 2           | <0.01       | 21          |
| 1751031     | 15.2        | 2.23        | 0.02        | <1          | <0.01       | 32          |
| 1751032     | 134         | 1.85        | 0.02        | 1           | <0.01       | 29          |
| 1751033     | 141         | 2.20        | 0.02        | 3           | <0.01       | 20          |
| 1751034     | 18.1        | 3.77        | <0.01       | <1          | <0.01       | 62          |
| 1751035     | 57.8        | 8.64        | <0.01       | <1          | <0.01       | 21          |
| 1751036     | 36.1        | 2.98        | <0.01       | <1          | <0.01       | 32          |
| 1751037     | 149         | 2.45        | 0.02        | 1           | <0.01       | 25          |
| 1751038     | 115         | 3.89        | 0.01        | <1          | <0.01       | 36          |
| 1751039     | 104         | 2.30        | 0.01        | <1          | <0.01       | 34          |

- not analysed | -- element not determined | I.S. insufficient sample | L.N.R. listed not received



Order Number PANCON\_RESOURCES  
 Project The Brewer Gold Project  
 Submission Number \*SD\* Pancon/ Brewer Gold B21C-  
 009/ 111 Core (1-56)  
 Number of Samples 56

## ANALYSIS REPORT BBM21-09948

| Element         | @Cu         | @Fe         | @K          | @Li         | @Mg         | @Mn         |
|-----------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Method          | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 |
| Lower Limit     | 0.5         | 0.01        | 0.01        | 1           | 0.01        | 2           |
| Upper Limit     | 10,000      | 15          | 15          | 10,000      | 15          | 10,000      |
| Unit            | ppm m / m   | %           | %           | ppm m / m   | %           | ppm m / m   |
| 1751041         | 114         | 1.66        | 0.01        | 1           | <0.01       | 21          |
| 1751042         | 97.4        | 1.97        | 0.03        | 2           | <0.01       | 33          |
| 1751043         | 68.1        | 3.05        | 0.02        | 3           | <0.01       | 18          |
| 1751044         | 72.3        | 1.27        | 0.03        | 2           | <0.01       | 36          |
| 1751045         | 76.8        | 1.64        | 0.03        | 2           | <0.01       | 23          |
| 1751046         | 16.0        | 1.56        | 0.01        | <1          | <0.01       | 47          |
| 1751047         | 28.8        | 0.70        | 0.02        | 1           | <0.01       | 20          |
| 1751048         | 52.0        | 1.89        | 0.01        | <1          | <0.01       | 52          |
| 1751049         | 127         | 2.60        | 0.07        | 2           | <0.01       | 27          |
| 1751051         | 334         | 3.23        | 0.07        | <1          | <0.01       | 24          |
| 1751052         | 1350        | 2.94        | 0.01        | <1          | <0.01       | 37          |
| 1751053         | 401         | 2.88        | 0.02        | <1          | <0.01       | 27          |
| 1751054         | 74.7        | 1.85        | 0.03        | <1          | <0.01       | 54          |
| 1751055         | 114         | 1.95        | 0.04        | <1          | <0.01       | 35          |
| 1751056         | 1684        | 1.73        | 0.02        | <1          | <0.01       | 43          |
| *Dup 1751039    | 106         | 2.06        | 0.01        | <1          | <0.01       | 24          |
| *Rep 1751053    | 417         | 2.95        | 0.02        | <1          | <0.01       | 28          |
| *Std OREAS 905  | 1488        | 3.84        | 2.93        | 20          | 0.28        | 357         |
| *Blk BLANK      | <0.5        | <0.01       | <0.01       | <1          | <0.01       | <2          |
| *Blk BLANK      | <0.5        | <0.01       | <0.01       | <1          | <0.01       | <2          |
| *Std OREAS 601b | 967         | 2.29        | 2.37        | 22          | 0.09        | 222         |
| *Std OREAS 601b | 963         | 2.20        | 2.41        | 21          | 0.09        | 202         |
| *Std OREAS 905  | 1453        | 3.96        | 2.94        | 19          | 0.28        | 341         |
| *Blk BLANK      | <0.5        | <0.01       | <0.01       | <1          | <0.01       | <2          |
| *Rep 1751038    | 109         | 3.85        | 0.01        | <1          | <0.01       | 36          |

- not analysed | -- element not determined | I.S. insufficient sample | L.N.R. listed not received



Order Number PANCON\_RESOURCES  
 Project The Brewer Gold Project  
 Submission Number \*SD\* Pancon/ Brewer Gold B21C-  
 009/ 111 Core (1-56)  
 Number of Samples 56

**ANALYSIS REPORT BBM21-09948**

| Element     | @Na         | @Ni         | @P          | @S          | @Sr         | @Ti         |
|-------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Method      | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 |
| Lower Limit | 0.01        | 1           | 0.01        | 0.01        | 0.5         | 0.01        |
| Upper Limit | 15          | 10,000      | 15          | 5           | 10,000      | 15          |
| Unit        | %           | ppm m / m   | %           | %           | ppm m / m   | %           |
| 1751001     | 0.01        | 2           | 0.02        | 0.47        | 148         | 0.04        |
| 1751002     | <0.01       | 1           | 0.02        | 0.38        | 165         | 0.05        |
| 1751003     | <0.01       | 2           | 0.01        | 0.03        | 114         | 0.05        |
| 1751004     | <0.01       | 1           | 0.02        | 0.11        | 123         | 0.05        |
| 1751005     | <0.01       | 2           | 0.03        | 0.04        | 157         | 0.05        |
| 1751006     | <0.01       | 5           | <0.01       | 2.94        | 28.1        | 0.05        |
| 1751007     | <0.01       | 3           | 0.01        | 0.41        | 55.8        | 0.04        |
| 1751008     | <0.01       | 1           | 0.01        | 0.10        | 93.5        | 0.05        |
| 1751009     | <0.01       | 3           | <0.01       | 0.03        | 38.2        | 0.03        |
| 1751011     | <0.01       | 6           | 0.01        | 2.93        | 98.8        | 0.03        |
| 1751012     | <0.01       | 5           | 0.03        | 2.24        | 214         | 0.03        |
| 1751013     | <0.01       | 3           | 0.03        | 1.34        | 258         | 0.04        |
| 1751014     | <0.01       | 2           | 0.04        | 0.56        | 333         | 0.05        |
| 1751015     | <0.01       | 2           | 0.03        | 0.53        | 259         | 0.05        |
| 1751016     | <0.01       | 2           | 0.03        | 0.04        | 237         | 0.05        |
| 1751017     | <0.01       | 1           | 0.03        | 0.05        | 262         | 0.05        |
| 1751018     | 0.01        | 2           | 0.06        | 0.07        | 316         | 0.05        |
| 1751019     | 0.02        | 4           | 0.06        | 2.80        | 437         | 0.05        |
| 1751021     | 0.01        | 6           | 0.03        | 3.39        | 240         | 0.04        |
| 1751022     | 0.01        | 4           | 0.03        | 2.49        | 225         | 0.04        |
| 1751023     | <0.01       | 3           | 0.02        | 0.04        | 105         | 0.02        |
| 1751024     | 0.01        | 3           | 0.04        | 1.61        | 278         | 0.04        |
| 1751025     | 0.02        | 3           | 0.03        | 2.29        | 184         | 0.05        |
| 1751026     | 0.01        | 3           | 0.06        | 2.06        | 302         | 0.05        |
| 1751027     | 0.01        | 3           | 0.12        | 0.77        | 273         | 0.03        |
| 1751028     | 0.02        | 2           | 0.06        | 1.10        | 352         | 0.05        |
| 1751029     | 0.02        | 2           | 0.08        | 0.45        | 384         | 0.04        |
| 1751031     | 0.02        | 2           | 0.04        | 0.06        | 251         | 0.03        |
| 1751032     | 0.02        | 3           | 0.07        | 1.58        | 323         | 0.05        |

- not analysed | -- element not determined | I.S. insufficient sample | L.N.R. listed not received



Order Number PANCON\_RESOURCES  
 Project The Brewer Gold Project  
 Submission Number \*SD\* Pancon/ Brewer Gold B21C-  
 009/ 111 Core (1-56)  
 Number of Samples 56

## ANALYSIS REPORT BBM21-09948

| Element         | @Na         | @Ni         | @P          | @S          | @Sr         | @Ti         |
|-----------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Method          | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 |
| Lower Limit     | 0.01        | 1           | 0.01        | 0.01        | 0.5         | 0.01        |
| Upper Limit     | 15          | 10,000      | 15          | 5           | 10,000      | 15          |
| Unit            | %           | ppm m / m   | %           | %           | ppm m / m   | %           |
| 1751033         | 0.02        | 3           | 0.06        | 1.74        | 304         | 0.04        |
| 1751034         | 0.01        | 2           | 0.05        | 0.06        | 231         | 0.02        |
| 1751035         | 0.01        | 3           | 0.06        | 0.32        | 321         | 0.02        |
| 1751036         | 0.01        | 2           | 0.07        | 0.47        | 458         | 0.04        |
| 1751037         | 0.01        | 4           | 0.04        | 2.27        | 205         | 0.03        |
| 1751038         | 0.01        | 5           | 0.03        | 4.11        | 145         | 0.03        |
| 1751039         | 0.01        | 3           | 0.04        | 2.04        | 205         | 0.04        |
| 1751041         | 0.01        | 3           | 0.05        | 1.36        | 285         | 0.06        |
| 1751042         | 0.01        | 3           | 0.07        | 1.40        | 348         | 0.06        |
| 1751043         | 0.02        | 3           | 0.07        | 1.14        | 396         | 0.03        |
| 1751044         | 0.02        | 2           | 0.06        | 1.07        | 356         | 0.05        |
| 1751045         | 0.02        | 3           | 0.08        | 1.22        | 280         | 0.05        |
| 1751046         | <0.01       | 1           | 0.01        | 0.10        | 72.7        | 0.04        |
| 1751047         | 0.01        | 2           | 0.02        | 0.58        | 145         | 0.07        |
| 1751048         | 0.01        | 3           | 0.04        | 1.52        | 270         | 0.04        |
| 1751049         | 0.02        | 5           | 0.13        | 2.51        | 711         | 0.04        |
| 1751051         | 0.02        | 5           | 0.06        | 3.62        | 277         | 0.05        |
| 1751052         | 0.01        | 4           | 0.14        | 3.25        | 464         | 0.09        |
| 1751053         | 0.01        | 7           | 0.11        | 3.37        | 262         | 0.04        |
| 1751054         | 0.02        | 3           | 0.09        | 1.58        | 217         | 0.05        |
| 1751055         | 0.02        | 5           | 0.12        | 1.98        | 224         | 0.04        |
| 1751056         | 0.01        | 4           | 0.11        | 1.65        | 194         | 0.06        |
| *Dup 1751039    | <0.01       | 3           | 0.04        | 2.04        | 203         | 0.04        |
| *Rep 1751053    | 0.01        | 6           | 0.10        | 3.34        | 266         | 0.04        |
| *Std OREAS 905  | 2.34        | 9           | 0.03        | 0.08        | 159         | 0.11        |
| *Blk BLANK      | <0.01       | <1          | <0.01       | <0.01       | <0.5        | <0.01       |
| *Blk BLANK      | <0.01       | <1          | <0.01       | <0.01       | <0.5        | <0.01       |
| *Std OREAS 601b | 1.88        | 6           | 0.03        | 1.45        | 242         | 0.12        |
| *Std OREAS 601b | 1.80        | 6           | 0.03        | 1.50        | 230         | 0.13        |

- not analysed | -- element not determined | I.S. insufficient sample | L.N.R. listed not received





Order Number PANCON\_RESOURCES  
 Project The Brewer Gold Project  
 Submission Number \*SD\* Pancon/ Brewer Gold B21C-  
 009/ 111 Core (1-56)  
 Number of Samples 56

**ANALYSIS REPORT BBM21-09948**

| Element        | @Na         | @Ni         | @P          | @S          | @Sr         | @Ti         |
|----------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Method         | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 |
| Lower Limit    | 0.01        | 1           | 0.01        | 0.01        | 0.5         | 0.01        |
| Upper Limit    | 15          | 10,000      | 15          | 5           | 10,000      | 15          |
| Unit           | %           | ppm m / m   | %           | %           | ppm m / m   | %           |
| *Std OREAS 905 | 2.35        | 9           | 0.03        | 0.07        | 150         | 0.11        |
| *Blk BLANK     | <0.01       | <1          | <0.01       | <0.01       | <0.5        | <0.01       |
| *Rep 1751038   | 0.01        | 5           | 0.03        | 4.07        | 143         | 0.03        |

| Element     | @V          | @Zn         | @Zr         | @Ag         | @As         | @Be         |
|-------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Method      | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 |
| Lower Limit | 2           | 1           | 0.5         | 0.02        | 1           | 0.1         |
| Upper Limit | 10,000      | 10,000      | 10,000      | 100         | 10,000      | 2,500       |
| Unit        | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   |
| 1751001     | 3           | 1           | 80.1        | 0.28        | 28          | <0.1        |
| 1751002     | 4           | <1          | 87.7        | 0.43        | 24          | <0.1        |
| 1751003     | 3           | 1           | 51.0        | 0.13        | 7           | <0.1        |
| 1751004     | 4           | <1          | 78.8        | 0.25        | 11          | <0.1        |
| 1751005     | 6           | <1          | 82.2        | 0.14        | 12          | <0.1        |
| 1751006     | <2          | <1          | 106         | 0.22        | 17          | <0.1        |
| 1751007     | 3           | <1          | 96.8        | 0.52        | 37          | <0.1        |
| 1751008     | 4           | <1          | 77.1        | 0.42        | 9           | <0.1        |
| 1751009     | 4           | 1           | 48.9        | 0.13        | 4           | <0.1        |
| 1751011     | 3           | <1          | 80.8        | 0.44        | 12          | <0.1        |
| 1751012     | <2          | <1          | 69.8        | 0.67        | 9           | <0.1        |
| 1751013     | 3           | 1           | 78.8        | 0.40        | 14          | <0.1        |
| 1751014     | 5           | 3           | 79.0        | 0.46        | 14          | <0.1        |
| 1751015     | 4           | 1           | 73.9        | 0.18        | 9           | <0.1        |
| 1751016     | 4           | <1          | 39.5        | 0.08        | 10          | <0.1        |
| 1751017     | 10          | <1          | 81.3        | 0.44        | 12          | <0.1        |
| 1751018     | 9           | 1           | 41.5        | 0.69        | 6           | <0.1        |
| 1751019     | 6           | 1           | 89.8        | 0.36        | 17          | 0.1         |
| 1751021     | 5           | 2           | 76.5        | 0.14        | 13          | <0.1        |

- not analysed | -- element not determined | I.S. insufficient sample | L.N.R. listed not received



Order Number PANCON\_RESOURCES  
 Project The Brewer Gold Project  
 Submission Number \*SD\* Pancon/ Brewer Gold B21C-  
 009/ 111 Core (1-56)  
 Number of Samples 56

## ANALYSIS REPORT BBM21-09948

| Element     | @V          | @Zn         | @Zr         | @Ag         | @As         | @Be         |
|-------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Method      | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 |
| Lower Limit | 2           | 1           | 0.5         | 0.02        | 1           | 0.1         |
| Upper Limit | 10,000      | 10,000      | 10,000      | 100         | 10,000      | 2,500       |
| Unit        | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   |
| 1751022     | 5           | 2           | 71.9        | 0.29        | 12          | 0.1         |
| 1751023     | 6           | 1           | 35.3        | 0.16        | 136         | <0.1        |
| 1751024     | 7           | 1           | 82.3        | 0.22        | 11          | 0.1         |
| 1751025     | 8           | <1          | 91.6        | 0.18        | 7           | <0.1        |
| 1751026     | 10          | <1          | 99.5        | 0.15        | 12          | 0.1         |
| 1751027     | 9           | <1          | 63.6        | 0.07        | 19          | 0.2         |
| 1751028     | 11          | <1          | 85.2        | 0.34        | 14          | 0.2         |
| 1751029     | 11          | <1          | 79.9        | 0.25        | 28          | 0.3         |
| 1751031     | 7           | 1           | 52.0        | 0.13        | 65          | 0.1         |
| 1751032     | 9           | 1           | 86.9        | 0.24        | 7           | 0.1         |
| 1751033     | 10          | 1           | 85.1        | 0.15        | 19          | 0.2         |
| 1751034     | 5           | <1          | 53.2        | 0.09        | 178         | 0.1         |
| 1751035     | 12          | <1          | 83.1        | 0.18        | 772         | 0.2         |
| 1751036     | 5           | 1           | 82.8        | 0.17        | 69          | 0.1         |
| 1751037     | 6           | 1           | 71.1        | 0.07        | 8           | <0.1        |
| 1751038     | 7           | <1          | 81.8        | 0.04        | 8           | <0.1        |
| 1751039     | 7           | 1           | 75.9        | 0.12        | 6           | <0.1        |
| 1751041     | 9           | 1           | 91.9        | 0.14        | 20          | 0.1         |
| 1751042     | 13          | <1          | 101         | 0.05        | 15          | 0.1         |
| 1751043     | 9           | <1          | 101         | 0.20        | 43          | 0.2         |
| 1751044     | 10          | <1          | 96.9        | 0.09        | 7           | 0.1         |
| 1751045     | 8           | <1          | 92.3        | <0.02       | 28          | 0.1         |
| 1751046     | 4           | 2           | 53.6        | 0.12        | 50          | <0.1        |
| 1751047     | 7           | <1          | 89.5        | <0.02       | 4           | <0.1        |
| 1751048     | 7           | 2           | 71.3        | 0.07        | 7           | <0.1        |
| 1751049     | 12          | <1          | 72.4        | 0.11        | 11          | 0.2         |
| 1751051     | 9           | <1          | 93.3        | 0.53        | 8           | <0.1        |
| 1751052     | 7           | 2           | 186         | 1.47        | 14          | 0.1         |
| 1751053     | 7           | 1           | 101         | 0.20        | 9           | <0.1        |

- not analysed | -- element not determined | I.S. insufficient sample | L.N.R. listed not received



Order Number PANCON\_RESOURCES  
 Project The Brewer Gold Project  
 Submission Number \*SD\* Pancon/ Brewer Gold B21C-  
 009/ 111 Core (1-56)  
 Number of Samples 56

## ANALYSIS REPORT BBM21-09948

| Element         | @V          | @Zn         | @Zr         | @Ag         | @As         | @Be         |
|-----------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Method          | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 |
| Lower Limit     | 2           | 1           | 0.5         | 0.02        | 1           | 0.1         |
| Upper Limit     | 10,000      | 10,000      | 10,000      | 100         | 10,000      | 2,500       |
| Unit            | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   |
| 1751054         | 11          | <1          | 89.3        | 0.05        | 4           | <0.1        |
| 1751055         | 13          | <1          | 94.6        | 0.12        | 4           | <0.1        |
| 1751056         | 11          | 1           | 98.3        | 2.13        | 6           | <0.1        |
| *Dup 1751039    | 7           | <1          | 80.0        | 0.29        | 6           | <0.1        |
| *Rep 1751053    | 7           | <1          | 101         | 0.16        | 9           | <0.1        |
| *Std OREAS 905  | 9           | 135         | 245         | 0.64        | 35          | 2.7         |
| *Blk BLANK      | <2          | 1           | <0.5        | <0.02       | <1          | <0.1        |
| *Blk BLANK      | <2          | <1          | <0.5        | <0.02       | <1          | <0.1        |
| *Std OREAS 601b | 11          | 295         | 174         | 48.50       | 302         | 2.2         |
| *Std OREAS 601b | 11          | 300         | 173         | 50.42       | 287         | 2.4         |
| *Std OREAS 905  | 9           | 132         | 236         | 0.54        | 33          | 3.0         |
| *Blk BLANK      | <2          | 1           | <0.5        | 0.03        | <1          | <0.1        |
| *Rep 1751038    | 7           | <1          | 81.4        | 0.03        | 8           | <0.1        |

| Element     | @Bi         | @Cd         | @Ce         | @Co         | @Cs         | @Ga         |
|-------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Method      | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 |
| Lower Limit | 0.04        | 0.02        | 0.05        | 0.1         | 1           | 0.1         |
| Upper Limit | 10,000      | 10,000      | 1,000       | 10,000      | 1,000       | 1,000       |
| Unit        | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   |
| 1751001     | 6.51        | 0.03        | 40.99       | 2.0         | <1          | 0.8         |
| 1751002     | 6.06        | 0.02        | 47.31       | 1.8         | <1          | 0.6         |
| 1751003     | 3.08        | <0.02       | 42.13       | 0.2         | <1          | 0.4         |
| 1751004     | 4.22        | 0.03        | 47.10       | 0.8         | <1          | 0.6         |
| 1751005     | 7.39        | <0.02       | 59.97       | 0.2         | <1          | 0.7         |
| 1751006     | 4.77        | 0.04        | 9.54        | 12.4        | <1          | 0.2         |
| 1751007     | 12.26       | 0.11        | 21.77       | 2.3         | <1          | 0.5         |
| 1751008     | 9.44        | <0.02       | 39.92       | 0.7         | <1          | 0.4         |
| 1751009     | 3.10        | 0.02        | 11.08       | 0.4         | <1          | 0.3         |

- not analysed | -- element not determined | I.S. insufficient sample | L.N.R. listed not received



Order Number PANCON\_RESOURCES  
 Project The Brewer Gold Project  
 Submission Number \*SD\* Pancon/ Brewer Gold B21C-  
 009/ 111 Core (1-56)  
 Number of Samples 56

## ANALYSIS REPORT BBM21-09948

| Element     | @Bi         | @Cd         | @Ce         | @Co         | @Cs         | @Ga         |
|-------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Method      | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 |
| Lower Limit | 0.04        | 0.02        | 0.05        | 0.1         | 1           | 0.1         |
| Upper Limit | 10,000      | 10,000      | 1,000       | 10,000      | 1,000       | 1,000       |
| Unit        | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   |
| 1751011     | 8.17        | 0.04        | 22.42       | 10.2        | <1          | 0.4         |
| 1751012     | 10.20       | <0.02       | 32.85       | 8.5         | <1          | 0.7         |
| 1751013     | 8.51        | 0.04        | 41.78       | 6.7         | <1          | 0.6         |
| 1751014     | 2.94        | 0.03        | 62.11       | 3.0         | <1          | 0.7         |
| 1751015     | 2.68        | 0.02        | 55.45       | 2.5         | <1          | 0.6         |
| 1751016     | 4.15        | <0.02       | 53.21       | 0.1         | <1          | 0.9         |
| 1751017     | 5.37        | <0.02       | 42.27       | 0.2         | <1          | 8.8         |
| 1751018     | 8.86        | 0.04        | 61.45       | 0.1         | <1          | 9.8         |
| 1751019     | 6.77        | 0.06        | 40.96       | 6.4         | <1          | 12.6        |
| 1751021     | 4.63        | 0.07        | 37.28       | 8.1         | <1          | 10.7        |
| 1751022     | 6.95        | 0.08        | 40.88       | 6.8         | <1          | 11.0        |
| 1751023     | 3.08        | 0.04        | 18.14       | 0.2         | <1          | 5.0         |
| 1751024     | 4.11        | 0.07        | 39.91       | 4.7         | <1          | 11.9        |
| 1751025     | 3.00        | 0.05        | 42.48       | 6.5         | <1          | 11.5        |
| 1751026     | 3.56        | 0.03        | 42.50       | 5.1         | <1          | 13.6        |
| 1751027     | 4.30        | <0.02       | 59.65       | 1.5         | <1          | 12.9        |
| 1751028     | 7.24        | 0.03        | 49.31       | 2.3         | <1          | 13.8        |
| 1751029     | 6.38        | <0.02       | 53.29       | 0.8         | <1          | 13.8        |
| 1751031     | 6.85        | <0.02       | 62.23       | 0.2         | <1          | 7.9         |
| 1751032     | 4.68        | 0.05        | 47.35       | 5.5         | <1          | 13.8        |
| 1751033     | 5.24        | 0.10        | 55.60       | 5.6         | <1          | 17.8        |
| 1751034     | 11.19       | <0.02       | 52.46       | 0.2         | <1          | 7.5         |
| 1751035     | 13.61       | <0.02       | 57.12       | 1.2         | <1          | 22.5        |
| 1751036     | 6.02        | 0.03        | 54.71       | 1.1         | <1          | 17.1        |
| 1751037     | 2.42        | 0.05        | 42.91       | 6.5         | <1          | 17.2        |
| 1751038     | 2.58        | 0.04        | 38.25       | 10.2        | <1          | 15.6        |
| 1751039     | 2.74        | 0.03        | 43.00       | 6.4         | <1          | 15.8        |
| 1751041     | 4.08        | 0.05        | 48.43       | 5.2         | <1          | 16.3        |
| 1751042     | 2.28        | 0.03        | 66.88       | 8.0         | <1          | 22.4        |

- not analysed | -- element not determined | I.S. insufficient sample | L.N.R. listed not received



Order Number PANCON\_RESOURCES  
 Project The Brewer Gold Project  
 Submission Number \*SD\* Pancon/ Brewer Gold B21C-  
 009/ 111 Core (1-56)  
 Number of Samples 56

## ANALYSIS REPORT BBM21-09948

| Element         | @Bi         | @Cd         | @Ce         | @Co         | @Cs         | @Ga         |
|-----------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Method          | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 |
| Lower Limit     | 0.04        | 0.02        | 0.05        | 0.1         | 1           | 0.1         |
| Upper Limit     | 10,000      | 10,000      | 1,000       | 10,000      | 1,000       | 1,000       |
| Unit            | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   |
| 1751043         | 2.57        | <0.02       | 84.94       | 4.3         | <1          | 18.2        |
| 1751044         | 1.66        | 0.02        | 65.65       | 5.4         | <1          | 25.5        |
| 1751045         | 1.97        | 0.02        | 53.13       | 6.9         | <1          | 29.5        |
| 1751046         | 0.66        | <0.02       | 14.00       | 0.5         | <1          | 7.6         |
| 1751047         | 0.69        | 0.02        | 29.33       | 2.8         | <1          | 14.8        |
| 1751048         | 1.83        | 0.03        | 57.78       | 10.6        | <1          | 12.9        |
| 1751049         | 3.88        | 0.03        | 98.85       | 17.2        | <1          | 22.1        |
| 1751051         | 12.75       | <0.02       | 54.48       | 19.3        | <1          | 12.5        |
| 1751052         | 52.62       | 0.07        | 137         | 22.6        | <1          | 16.0        |
| 1751053         | 6.50        | 0.05        | 79.40       | 17.3        | <1          | 11.0        |
| 1751054         | 2.12        | <0.02       | 65.53       | 8.2         | <1          | 11.5        |
| 1751055         | 2.24        | <0.02       | 58.01       | 10.4        | <1          | 11.5        |
| 1751056         | 59.28       | <0.02       | 61.01       | 9.9         | <1          | 11.6        |
| *Dup 1751039    | 2.85        | 0.05        | 45.83       | 6.3         | <1          | 15.9        |
| *Rep 1751053    | 6.56        | 0.06        | 80.74       | 18.7        | <1          | 11.8        |
| *Std OREAS 905  | 5.78        | 0.71        | 90.79       | 14.8        | 7           | 25.7        |
| *Blk BLANK      | <0.04       | <0.02       | 0.11        | <0.1        | <1          | <0.1        |
| *Blk BLANK      | <0.04       | <0.02       | 0.12        | <0.1        | <1          | <0.1        |
| *Std OREAS 601b | 18.07       | 1.96        | 73.96       | 3.0         | 5           | 23.4        |
| *Std OREAS 601b | 16.76       | 2.06        | 68.02       | 3.1         | 5           | 23.6        |
| *Std OREAS 905  | 5.49        | 0.36        | 90.94       | 15.5        | 7           | 24.9        |
| *Blk BLANK      | <0.04       | <0.02       | <0.05       | <0.1        | <1          | <0.1        |
| *Rep 1751038    | 2.59        | 0.04        | 35.39       | 9.8         | <1          | 15.5        |

- not analysed | -- element not determined | I.S. insufficient sample | L.N.R. listed not received



Order Number PANCON\_RESOURCES  
 Project The Brewer Gold Project  
 Submission Number \*SD\* Pancon/ Brewer Gold B21C-  
 009/ 111 Core (1-56)  
 Number of Samples 56

## ANALYSIS REPORT BBM21-09948

| Element     | @Hf         | @In         | @La         | @Lu         | @Mo         | @Nb         |
|-------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Method      | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 |
| Lower Limit | 0.02        | 0.02        | 0.1         | 0.01        | 0.05        | 0.1         |
| Upper Limit | 500         | 500         | 10,000      | 1,000       | 10,000      | 1,000       |
| Unit        | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   |
| 1751001     | 2.33        | 0.03        | 19.6        | 0.18        | 9.05        | 1.3         |
| 1751002     | 2.54        | 0.03        | 22.8        | 0.19        | 14.22       | 1.6         |
| 1751003     | 1.43        | <0.02       | 20.7        | 0.15        | 7.14        | 1.2         |
| 1751004     | 2.28        | 0.03        | 21.8        | 0.17        | 16.75       | 1.8         |
| 1751005     | 2.33        | <0.02       | 27.7        | 0.19        | 11.13       | 1.5         |
| 1751006     | 3.10        | <0.02       | 5.1         | 0.18        | 19.91       | 1.6         |
| 1751007     | 2.74        | 0.02        | 11.7        | 0.20        | 36.48       | 1.5         |
| 1751008     | 2.34        | <0.02       | 19.3        | 0.17        | 10.21       | 1.7         |
| 1751009     | 1.44        | <0.02       | 6.2         | 0.10        | 3.89        | 1.0         |
| 1751011     | 2.32        | <0.02       | 12.3        | 0.16        | 18.80       | 1.3         |
| 1751012     | 2.14        | <0.02       | 17.0        | 0.14        | 20.89       | 1.1         |
| 1751013     | 2.30        | <0.02       | 19.2        | 0.16        | 24.45       | 1.4         |
| 1751014     | 2.28        | 0.03        | 30.4        | 0.17        | 21.11       | 1.6         |
| 1751015     | 2.30        | <0.02       | 25.8        | 0.18        | 11.29       | 1.7         |
| 1751016     | 0.66        | <0.02       | 24.7        | 0.19        | 9.68        | 0.9         |
| 1751017     | 2.32        | 0.04        | 20.2        | 0.21        | 15.66       | 1.7         |
| 1751018     | 0.92        | 0.03        | 31.9        | 0.20        | 6.01        | 1.0         |
| 1751019     | 2.75        | <0.02       | 18.5        | 0.21        | 15.64       | 1.6         |
| 1751021     | 2.41        | <0.02       | 17.0        | 0.18        | 12.20       | 1.5         |
| 1751022     | 2.22        | <0.02       | 18.8        | 0.17        | 12.58       | 1.4         |
| 1751023     | 1.08        | 0.04        | 10.0        | 0.08        | 11.49       | 0.6         |
| 1751024     | 2.49        | <0.02       | 18.1        | 0.19        | 17.91       | 1.6         |
| 1751025     | 2.75        | <0.02       | 20.4        | 0.19        | 23.43       | 2.0         |
| 1751026     | 2.98        | <0.02       | 18.9        | 0.20        | 18.07       | 1.9         |
| 1751027     | 1.92        | <0.02       | 27.8        | 0.13        | 7.67        | 1.0         |
| 1751028     | 2.49        | <0.02       | 23.5        | 0.18        | 16.43       | 1.6         |
| 1751029     | 2.34        | 0.02        | 25.3        | 0.14        | 19.69       | 1.1         |
| 1751031     | 1.56        | 0.03        | 30.2        | 0.09        | 9.93        | 0.8         |
| 1751032     | 2.65        | <0.02       | 22.1        | 0.18        | 26.89       | 1.8         |

- not analysed | -- element not determined | I.S. insufficient sample | L.N.R. listed not received



Order Number PANCON\_RESOURCES  
 Project The Brewer Gold Project  
 Submission Number \*SD\* Pancon/ Brewer Gold B21C-  
 009/ 111 Core (1-56)  
 Number of Samples 56

**ANALYSIS REPORT BBM21-09948**

| Element         | @Hf         | @In         | @La         | @Lu         | @Mo         | @Nb         |
|-----------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Method          | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 |
| Lower Limit     | 0.02        | 0.02        | 0.1         | 0.01        | 0.05        | 0.1         |
| Upper Limit     | 500         | 500         | 10,000      | 1,000       | 10,000      | 1,000       |
| Unit            | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   |
| 1751033         | 2.55        | <0.02       | 26.4        | 0.16        | 24.18       | 1.3         |
| 1751034         | 1.60        | 0.07        | 26.7        | 0.09        | 17.65       | 0.7         |
| 1751035         | 2.50        | 0.25        | 27.9        | 0.15        | 34.22       | 0.7         |
| 1751036         | 2.47        | 0.04        | 23.9        | 0.16        | 26.98       | 1.3         |
| 1751037         | 2.15        | <0.02       | 21.3        | 0.14        | 20.62       | 1.2         |
| 1751038         | 2.50        | <0.02       | 19.4        | 0.16        | 27.69       | 1.1         |
| 1751039         | 2.38        | <0.02       | 20.4        | 0.15        | 27.00       | 1.4         |
| 1751041         | 2.70        | <0.02       | 24.6        | 0.16        | 26.86       | 2.0         |
| 1751042         | 3.06        | <0.02       | 35.4        | 0.17        | 21.73       | 4.0         |
| 1751043         | 3.00        | 0.02        | 45.4        | 0.18        | 19.20       | 1.2         |
| 1751044         | 2.76        | <0.02       | 35.0        | 0.16        | 23.24       | 2.0         |
| 1751045         | 2.76        | <0.02       | 27.4        | 0.15        | 20.71       | 1.9         |
| 1751046         | 1.49        | <0.02       | 7.2         | 0.09        | 23.00       | 1.0         |
| 1751047         | 2.57        | <0.02       | 15.8        | 0.16        | 38.27       | 2.1         |
| 1751048         | 2.06        | <0.02       | 31.5        | 0.12        | 26.09       | 1.3         |
| 1751049         | 2.11        | <0.02       | 54.7        | 0.11        | 22.41       | 1.8         |
| 1751051         | 2.81        | 0.02        | 30.4        | 0.15        | 77.70       | 1.9         |
| 1751052         | 5.51        | 0.05        | 72.1        | 0.31        | 60.20       | 2.8         |
| 1751053         | 2.93        | <0.02       | 43.0        | 0.16        | 44.49       | 1.6         |
| 1751054         | 2.60        | <0.02       | 35.5        | 0.14        | 24.52       | 2.2         |
| 1751055         | 2.75        | <0.02       | 30.9        | 0.13        | 24.88       | 2.4         |
| 1751056         | 2.96        | 0.03        | 32.3        | 0.15        | 25.08       | 2.3         |
| *Dup 1751039    | 2.32        | <0.02       | 21.4        | 0.16        | 27.04       | 1.4         |
| *Rep 1751053    | 2.99        | <0.02       | 44.1        | 0.17        | 47.14       | 1.8         |
| *Std OREAS 905  | 7.15        | 0.71        | 46.6        | 0.10        | 3.44        | 18.7        |
| *Blk BLANK      | <0.02       | <0.02       | <0.1        | <0.01       | 0.10        | <0.1        |
| *Blk BLANK      | <0.02       | <0.02       | <0.1        | <0.01       | <0.05       | <0.1        |
| *Std OREAS 601b | 5.38        | 0.46        | 33.4        | 0.07        | 5.09        | 15.1        |
| *Std OREAS 601b | 5.41        | 0.49        | 32.9        | 0.07        | 5.96        | 15.5        |

- not analysed | -- element not determined | I.S. insufficient sample | L.N.R. listed not received



Order Number PANCON\_RESOURCES  
 Project The Brewer Gold Project  
 Submission Number \*SD\* Pancon/ Brewer Gold B21C-  
 009/ 111 Core (1-56)  
 Number of Samples 56

**ANALYSIS REPORT BBM21-09948**

| Element        | @Hf         | @In         | @La         | @Lu         | @Mo         | @Nb         |
|----------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Method         | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 |
| Lower Limit    | 0.02        | 0.02        | 0.1         | 0.01        | 0.05        | 0.1         |
| Upper Limit    | 500         | 500         | 10,000      | 1,000       | 10,000      | 1,000       |
| Unit           | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   |
| *Std OREAS 905 | 7.66        | 0.65        | 47.6        | 0.10        | 3.00        | 19.3        |
| *Blk BLANK     | <0.02       | <0.02       | <0.1        | <0.01       | <0.05       | <0.1        |
| *Rep 1751038   | 2.47        | <0.02       | 19.0        | 0.15        | 27.42       | 1.0         |

| Element     | @Pb         | @Rb         | @Sb         | @Sc         | @Se         | @Sn         |
|-------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Method      | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 |
| Lower Limit | 0.5         | 0.2         | 0.05        | 0.5         | 2           | 0.3         |
| Upper Limit | 10,000      | 10,000      | 10,000      | 10,000      | 1,000       | 1,000       |
| Unit        | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   |
| 1751001     | 90.1        | 0.2         | 5.30        | 3.1         | 26          | 4.4         |
| 1751002     | 99.3        | <0.2        | 6.96        | 3.4         | 31          | 4.6         |
| 1751003     | 51.0        | <0.2        | 2.26        | 2.5         | 9           | 3.7         |
| 1751004     | 60.9        | <0.2        | 3.80        | 3.0         | 13          | 4.4         |
| 1751005     | 111         | <0.2        | 2.88        | 3.5         | 11          | 4.2         |
| 1751006     | 20.0        | <0.2        | 1.60        | 3.1         | 34          | 4.2         |
| 1751007     | 31.0        | <0.2        | 4.21        | 3.8         | 81          | 6.0         |
| 1751008     | 51.7        | <0.2        | 3.03        | 3.0         | 14          | 4.5         |
| 1751009     | 18.9        | <0.2        | 1.53        | 1.7         | 3           | 2.8         |
| 1751011     | 59.1        | <0.2        | 2.58        | 2.6         | 52          | 4.3         |
| 1751012     | 171         | <0.2        | 2.10        | 2.1         | 49          | 3.4         |
| 1751013     | 160         | <0.2        | 3.75        | 2.6         | 32          | 3.5         |
| 1751014     | 224         | <0.2        | 3.99        | 3.2         | 21          | 3.5         |
| 1751015     | 177         | <0.2        | 3.40        | 3.0         | 15          | 3.6         |
| 1751016     | 107         | <0.2        | 6.30        | 3.2         | 9           | 3.5         |
| 1751017     | 155         | <0.2        | 11.03       | 3.7         | 26          | 3.7         |
| 1751018     | 150         | <0.2        | 4.73        | 3.3         | 3           | 3.5         |
| 1751019     | 290         | <0.2        | 2.26        | 2.9         | 24          | 4.3         |
| 1751021     | 154         | <0.2        | 0.86        | 3.0         | 22          | 2.8         |

- not analysed | -- element not determined | I.S. insufficient sample | L.N.R. listed not received





Order Number PANCON\_RESOURCES  
 Project The Brewer Gold Project  
 Submission Number \*SD\* Pancon/ Brewer Gold B21C-  
 009/ 111 Core (1-56)  
 Number of Samples 56

## ANALYSIS REPORT BBM21-09948

| Element     | @Pb         | @Rb         | @Sb         | @Sc         | @Se         | @Sn         |
|-------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Method      | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 |
| Lower Limit | 0.5         | 0.2         | 0.05        | 0.5         | 2           | 0.3         |
| Upper Limit | 10,000      | 10,000      | 10,000      | 10,000      | 1,000       | 1,000       |
| Unit        | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   |
| 1751022     | 103         | <0.2        | 0.78        | 2.8         | 16          | 2.4         |
| 1751023     | 41.8        | <0.2        | 8.97        | 1.5         | 10          | 1.2         |
| 1751024     | 127         | 0.2         | 2.53        | 3.0         | 20          | 2.6         |
| 1751025     | 73.5        | 0.3         | 0.49        | 3.1         | 14          | 2.7         |
| 1751026     | 167         | 0.2         | 2.21        | 3.3         | 15          | 3.2         |
| 1751027     | 126         | 0.3         | 4.00        | 2.7         | 13          | 2.4         |
| 1751028     | 156         | 0.9         | 4.06        | 3.4         | 15          | 4.3         |
| 1751029     | 177         | 0.6         | 4.90        | 2.9         | 18          | 3.1         |
| 1751031     | 109         | 0.3         | 5.69        | 2.1         | 10          | 1.8         |
| 1751032     | 135         | 0.3         | 1.96        | 3.4         | 12          | 3.6         |
| 1751033     | 124         | 0.4         | 2.34        | 2.8         | 13          | 3.2         |
| 1751034     | 88.1        | <0.2        | 7.81        | 1.8         | 8           | 1.4         |
| 1751035     | 132         | <0.2        | 32.04       | 3.2         | 16          | 1.7         |
| 1751036     | 236         | <0.2        | 8.12        | 2.6         | 20          | 2.7         |
| 1751037     | 82.3        | 0.3         | 0.92        | 2.2         | 14          | 2.3         |
| 1751038     | 51.1        | 0.3         | 0.60        | 2.5         | 23          | 2.2         |
| 1751039     | 89.3        | 0.2         | 0.48        | 2.6         | 14          | 3.2         |
| 1751041     | 141         | 0.2         | 2.18        | 2.9         | 9           | 4.4         |
| 1751042     | 118         | 0.6         | 2.23        | 3.3         | 9           | 4.1         |
| 1751043     | 119         | 0.3         | 6.99        | 3.2         | 14          | 2.2         |
| 1751044     | 123         | 0.5         | 1.65        | 3.0         | 5           | 3.2         |
| 1751045     | 77.2        | 0.5         | 2.81        | 3.2         | 9           | 2.9         |
| 1751046     | 19.4        | 0.3         | 3.37        | 1.6         | 3           | 1.8         |
| 1751047     | 40.1        | 0.4         | 0.99        | 2.9         | 4           | 3.3         |
| 1751048     | 78.8        | 0.2         | 1.22        | 2.1         | 7           | 2.6         |
| 1751049     | 220         | 1.3         | 2.15        | 2.6         | 14          | 3.4         |
| 1751051     | 92.1        | 1.4         | 0.76        | 3.3         | 19          | 6.1         |
| 1751052     | 151         | 0.2         | 2.21        | 5.7         | 25          | 15.4        |
| 1751053     | 79.3        | 0.3         | 0.69        | 3.1         | 16          | 4.3         |

- not analysed | -- element not determined | I.S. insufficient sample | L.N.R. listed not received



Order Number PANCON\_RESOURCES  
 Project The Brewer Gold Project  
 Submission Number \*SD\* Pancon/ Brewer Gold B21C-  
 009/ 111 Core (1-56)  
 Number of Samples 56

## ANALYSIS REPORT BBM21-09948

| Element         | @Pb         | @Rb         | @Sb         | @Sc         | @Se         | @Sn         |
|-----------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Method          | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 |
| Lower Limit     | 0.5         | 0.2         | 0.05        | 0.5         | 2           | 0.3         |
| Upper Limit     | 10,000      | 10,000      | 10,000      | 10,000      | 1,000       | 1,000       |
| Unit            | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   |
| 1751054         | 68.2        | 0.6         | 0.38        | 2.9         | 7           | 4.0         |
| 1751055         | 80.4        | 0.7         | 0.40        | 2.9         | 8           | 4.1         |
| 1751056         | 73.7        | 0.4         | 0.79        | 3.3         | 24          | 8.8         |
| *Dup 1751039    | 86.0        | 0.2         | 0.52        | 2.8         | 13          | 3.3         |
| *Rep 1751053    | 81.2        | 0.3         | 0.74        | 3.4         | 15          | 4.4         |
| *Std OREAS 905  | 29.1        | 138         | 2.02        | 5.3         | 3           | 4.3         |
| *Blk BLANK      | <0.5        | <0.2        | <0.05       | <0.5        | <2          | <0.3        |
| *Blk BLANK      | <0.5        | <0.2        | <0.05       | <0.5        | <2          | <0.3        |
| *Std OREAS 601b | 306         | 95.0        | 22.31       | 4.4         | 9           | 3.1         |
| *Std OREAS 601b | 344         | 95.6        | 24.44       | 4.3         | 11          | 3.4         |
| *Std OREAS 905  | 29.5        | 130         | 1.94        | 5.9         | 3           | 4.0         |
| *Blk BLANK      | <0.5        | <0.2        | <0.05       | <0.5        | <2          | <0.3        |
| *Rep 1751038    | 49.9        | 0.3         | 0.55        | 2.5         | 23          | 2.0         |

| Element     | @Ta         | @Tb         | @Te         | @Th         | @Tl         | @U          |
|-------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Method      | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 |
| Lower Limit | 0.05        | 0.05        | 0.05        | 0.2         | 0.02        | 0.05        |
| Upper Limit | 10,000      | 10,000      | 1,000       | 10,000      | 10,000      | 10,000      |
| Unit        | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   |
| 1751001     | 0.09        | 0.21        | 13.19       | 6.3         | 0.08        | 0.98        |
| 1751002     | 0.09        | 0.22        | 26.86       | 7.5         | 0.07        | 1.04        |
| 1751003     | <0.05       | 0.18        | 9.07        | 6.4         | <0.02       | 0.77        |
| 1751004     | 0.08        | 0.21        | 18.83       | 7.6         | <0.02       | 0.96        |
| 1751005     | <0.05       | 0.28        | 7.10        | 10.3        | <0.02       | 1.20        |
| 1751006     | 0.10        | 0.10        | 9.86        | 3.3         | 0.17        | 0.97        |
| 1751007     | <0.05       | 0.15        | 17.03       | 5.2         | 0.04        | 1.05        |
| 1751008     | 0.09        | 0.28        | 8.71        | 7.0         | <0.02       | 0.99        |
| 1751009     | <0.05       | 0.09        | 2.46        | 2.1         | <0.02       | 0.49        |

- not analysed | -- element not determined | I.S. insufficient sample | L.N.R. listed not received



Order Number PANCON\_RESOURCES  
 Project The Brewer Gold Project  
 Submission Number \*SD\* Pancon/ Brewer Gold B21C-  
 009/ 111 Core (1-56)  
 Number of Samples 56

**ANALYSIS REPORT BBM21-09948**

| Element     | @Ta         | @Tb         | @Te         | @Th         | @Tl         | @U          |
|-------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Method      | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 |
| Lower Limit | 0.05        | 0.05        | 0.05        | 0.2         | 0.02        | 0.05        |
| Upper Limit | 10,000      | 10,000      | 1,000       | 10,000      | 10,000      | 10,000      |
| Unit        | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   |
| 1751011     | 0.08        | 0.14        | 8.51        | 4.6         | 0.11        | 0.86        |
| 1751012     | 0.07        | 0.17        | 4.77        | 5.6         | 0.05        | 0.79        |
| 1751013     | 0.07        | 0.19        | 9.66        | 6.0         | 0.12        | 0.86        |
| 1751014     | 0.07        | 0.28        | 22.71       | 7.9         | 0.08        | 1.01        |
| 1751015     | 0.09        | 0.26        | 9.24        | 7.9         | 0.07        | 0.97        |
| 1751016     | <0.05       | 0.22        | 8.37        | 7.9         | <0.02       | 0.93        |
| 1751017     | 0.06        | 0.22        | 27.61       | 7.2         | <0.02       | 1.00        |
| 1751018     | <0.05       | 0.23        | 6.19        | 9.2         | <0.02       | 1.07        |
| 1751019     | 0.10        | 0.24        | 6.06        | 7.0         | 0.03        | 1.17        |
| 1751021     | 0.10        | 0.20        | 4.62        | 6.8         | 0.04        | 1.02        |
| 1751022     | 0.10        | 0.18        | 3.74        | 7.3         | 0.03        | 0.92        |
| 1751023     | <0.05       | 0.12        | 9.66        | 3.0         | <0.02       | 0.45        |
| 1751024     | 0.11        | 0.22        | 7.44        | 6.8         | 0.03        | 1.03        |
| 1751025     | 0.12        | 0.16        | 4.41        | 7.2         | 0.03        | 1.05        |
| 1751026     | 0.12        | 0.18        | 5.64        | 6.7         | 0.04        | 1.09        |
| 1751027     | 0.06        | 0.19        | 5.13        | 8.9         | 0.02        | 0.71        |
| 1751028     | 0.10        | 0.19        | 3.69        | 8.1         | 0.07        | 0.90        |
| 1751029     | 0.06        | 0.20        | 4.52        | 7.4         | 0.05        | 0.78        |
| 1751031     | <0.05       | 0.16        | 4.72        | 9.5         | <0.02       | 0.54        |
| 1751032     | 0.11        | 0.17        | 4.27        | 7.9         | 0.03        | 0.97        |
| 1751033     | 0.08        | 0.20        | 3.09        | 8.8         | 0.03        | 0.95        |
| 1751034     | <0.05       | 0.16        | 7.55        | 7.1         | <0.02       | 0.56        |
| 1751035     | <0.05       | 0.22        | 40.25       | 8.3         | <0.02       | 0.96        |
| 1751036     | 0.05        | 0.22        | 13.34       | 7.6         | 0.04        | 0.88        |
| 1751037     | 0.07        | 0.18        | 2.30        | 7.0         | 0.04        | 0.84        |
| 1751038     | 0.07        | 0.16        | 2.87        | 6.4         | 0.07        | 0.93        |
| 1751039     | 0.08        | 0.17        | 2.41        | 7.0         | <0.02       | 0.90        |
| 1751041     | 0.12        | 0.18        | 5.05        | 7.4         | <0.02       | 1.03        |
| 1751042     | 0.66        | 0.20        | 2.84        | 10.7        | 0.03        | 1.06        |

- not analysed | -- element not determined | I.S. insufficient sample | L.N.R. listed not received



Order Number PANCON\_RESOURCES  
 Project The Brewer Gold Project  
 Submission Number \*SD\* Pancon/ Brewer Gold B21C-  
 009/ 111 Core (1-56)  
 Number of Samples 56

**ANALYSIS REPORT BBM21-09948**

| Element         | @Ta         | @Tb         | @Te         | @Th         | @Tl         | @U          |
|-----------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Method          | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 |
| Lower Limit     | 0.05        | 0.05        | 0.05        | 0.2         | 0.02        | 0.05        |
| Upper Limit     | 10,000      | 10,000      | 1,000       | 10,000      | 10,000      | 10,000      |
| Unit            | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   |
| 1751043         | 0.11        | 0.25        | 5.37        | 12.0        | <0.02       | 1.01        |
| 1751044         | 0.22        | 0.20        | 2.32        | 10.1        | 0.02        | 1.03        |
| 1751045         | 0.14        | 0.18        | 3.74        | 8.3         | 0.03        | 0.95        |
| 1751046         | <0.05       | 0.08        | 3.15        | 2.3         | <0.02       | 0.46        |
| 1751047         | 0.10        | 0.12        | 0.84        | 5.3         | <0.02       | 0.82        |
| 1751048         | 0.07        | 0.18        | 2.42        | 9.2         | <0.02       | 0.74        |
| 1751049         | 0.31        | 0.36        | 4.56        | 15.3        | 0.05        | 0.87        |
| 1751051         | 0.22        | 0.21        | 6.34        | 9.1         | 0.07        | 1.00        |
| 1751052         | 0.22        | 0.51        | 20.71       | 19.9        | 0.04        | 2.12        |
| 1751053         | 0.19        | 0.32        | 4.56        | 12.5        | 0.02        | 1.21        |
| 1751054         | 0.26        | 0.24        | 3.15        | 11.1        | 0.02        | 1.10        |
| 1751055         | 0.54        | 0.29        | 2.35        | 10.3        | 0.03        | 1.03        |
| 1751056         | 0.36        | 0.28        | 4.78        | 10.2        | <0.02       | 1.08        |
| *Dup 1751039    | 0.10        | 0.17        | 2.57        | 6.7         | <0.02       | 0.88        |
| *Rep 1751053    | 0.23        | 0.32        | 4.88        | 12.8        | 0.02        | 1.28        |
| *Std OREAS 905  | 1.41        | 0.82        | 0.08        | 14.5        | 0.77        | 5.20        |
| *Blk BLANK      | <0.05       | <0.05       | <0.05       | <0.2        | <0.02       | <0.05       |
| *Blk BLANK      | <0.05       | <0.05       | <0.05       | <0.2        | <0.02       | <0.05       |
| *Std OREAS 601b | 1.17        | 0.58        | 11.33       | 11.5        | 1.46        | 4.42        |
| *Std OREAS 601b | 1.05        | 0.51        | 12.12       | 12.5        | 1.53        | 4.56        |
| *Std OREAS 905  | 1.39        | 0.77        | 0.08        | 15.2        | 0.74        | 5.04        |
| *Blk BLANK      | <0.05       | <0.05       | 0.06        | <0.2        | <0.02       | <0.05       |
| *Rep 1751038    | 0.07        | 0.16        | 2.46        | 6.3         | 0.06        | 0.90        |

- not analysed | -- element not determined | I.S. insufficient sample | L.N.R. listed not received



Order Number PANCON\_RESOURCES  
 Project The Brewer Gold Project  
 Submission Number \*SD\* Pancon/ Brewer Gold B21C-  
 009/ 111 Core (1-56)  
 Number of Samples 56

**ANALYSIS REPORT BBM21-09948**

| Element     | @W          | @Y          | @Yb         | Dy          | Er          | Eu          |
|-------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Method      | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 |
| Lower Limit | 0.1         | 0.1         | 0.1         | 0.05        | 0.05        | 0.05        |
| Upper Limit | 10,000      | 10,000      | 1,000       | 1,000       | 1,000       | 500         |
| Unit        | ppm m / m   | ppm m / m   | ppm m / m   | mg / kg     | mg / kg     | mg / kg     |
| 1751001     | 0.9         | 5.2         | 1.0         | 1.04        | 0.76        | 0.65        |
| 1751002     | 0.9         | 5.6         | 1.1         | 1.06        | 0.86        | 0.76        |
| 1751003     | 0.8         | 4.6         | 0.9         | 0.86        | 0.67        | 0.64        |
| 1751004     | 0.7         | 5.2         | 1.0         | 1.02        | 0.77        | 0.76        |
| 1751005     | 0.9         | 5.8         | 1.2         | 1.23        | 0.91        | 0.96        |
| 1751006     | 1.0         | 4.8         | 1.0         | 0.66        | 0.68        | 0.18        |
| 1751007     | 1.1         | 5.7         | 1.1         | 0.89        | 0.84        | 0.39        |
| 1751008     | 0.8         | 5.3         | 1.0         | 1.14        | 0.75        | 0.86        |
| 1751009     | 1.0         | 2.7         | 0.5         | 0.48        | 0.39        | 0.22        |
| 1751011     | 0.8         | 4.6         | 0.9         | 0.78        | 0.66        | 0.38        |
| 1751012     | 0.7         | 4.4         | 0.9         | 0.87        | 0.62        | 0.55        |
| 1751013     | 0.7         | 4.9         | 0.9         | 0.88        | 0.71        | 0.64        |
| 1751014     | 0.8         | 5.7         | 1.0         | 1.16        | 0.77        | 0.92        |
| 1751015     | 0.8         | 6.0         | 1.0         | 1.21        | 0.91        | 0.83        |
| 1751016     | 0.8         | 6.4         | 1.1         | 1.15        | 0.88        | 0.81        |
| 1751017     | 1.1         | 6.4         | 1.2         | 1.13        | 0.90        | 0.72        |
| 1751018     | 0.9         | 6.3         | 1.1         | 1.13        | 0.87        | 0.86        |
| 1751019     | 1.1         | 6.0         | 1.2         | 1.19        | 0.86        | 0.76        |
| 1751021     | 0.9         | 5.8         | 1.1         | 1.06        | 0.80        | 0.65        |
| 1751022     | 0.8         | 5.7         | 1.1         | 0.98        | 0.81        | 0.66        |
| 1751023     | 0.4         | 3.0         | 0.5         | 0.58        | 0.41        | 0.40        |
| 1751024     | 1.1         | 6.2         | 1.1         | 1.14        | 0.87        | 0.73        |
| 1751025     | 1.3         | 5.7         | 1.1         | 0.89        | 0.80        | 0.62        |
| 1751026     | 1.3         | 5.3         | 1.1         | 0.93        | 0.74        | 0.60        |
| 1751027     | 0.9         | 3.9         | 0.8         | 0.86        | 0.59        | 0.87        |
| 1751028     | 1.2         | 4.9         | 1.0         | 0.91        | 0.72        | 0.78        |
| 1751029     | 0.8         | 4.0         | 0.8         | 0.87        | 0.59        | 0.87        |
| 1751031     | 0.5         | 2.5         | 0.5         | 0.64        | 0.39        | 0.84        |
| 1751032     | 1.2         | 4.4         | 1.0         | 0.83        | 0.69        | 0.78        |

- not analysed | -- element not determined | I.S. insufficient sample | L.N.R. listed not received



Order Number PANCON\_RESOURCES  
 Project The Brewer Gold Project  
 Submission Number \*SD\* Pancon/ Brewer Gold B21C-  
 009/ 111 Core (1-56)  
 Number of Samples 56

**ANALYSIS REPORT BBM21-09948**

| Element         | @W          | @Y          | @Yb         | Dy          | Er          | Eu          |
|-----------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Method          | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 |
| Lower Limit     | 0.1         | 0.1         | 0.1         | 0.05        | 0.05        | 0.05        |
| Upper Limit     | 10,000      | 10,000      | 1,000       | 1,000       | 1,000       | 500         |
| Unit            | ppm m / m   | ppm m / m   | ppm m / m   | mg / kg     | mg / kg     | mg / kg     |
| 1751033         | 0.9         | 4.3         | 0.9         | 0.91        | 0.64        | 0.85        |
| 1751034         | 0.4         | 2.4         | 0.5         | 0.62        | 0.37        | 0.69        |
| 1751035         | 0.6         | 3.8         | 0.8         | 0.96        | 0.60        | 0.86        |
| 1751036         | 0.7         | 4.4         | 0.8         | 1.00        | 0.65        | 0.90        |
| 1751037         | 0.8         | 4.1         | 0.8         | 0.87        | 0.59        | 0.71        |
| 1751038         | 0.7         | 4.4         | 0.9         | 0.84        | 0.64        | 0.59        |
| 1751039         | 0.9         | 4.6         | 0.9         | 0.80        | 0.64        | 0.68        |
| 1751041         | 1.0         | 3.9         | 0.9         | 0.76        | 0.56        | 0.70        |
| 1751042         | 1.2         | 3.9         | 0.9         | 0.77        | 0.54        | 0.92        |
| 1751043         | 0.5         | 4.6         | 1.0         | 0.93        | 0.62        | 1.13        |
| 1751044         | 0.7         | 3.7         | 0.8         | 0.75        | 0.49        | 0.87        |
| 1751045         | 0.6         | 3.6         | 0.8         | 0.73        | 0.48        | 0.74        |
| 1751046         | 2.9         | 1.9         | 0.5         | 0.34        | 0.27        | 0.25        |
| 1751047         | 1.9         | 3.2         | 0.8         | 0.54        | 0.47        | 0.46        |
| 1751048         | 0.6         | 2.9         | 0.6         | 0.64        | 0.40        | 0.81        |
| 1751049         | 0.9         | 3.5         | 0.6         | 1.17        | 0.40        | 1.34        |
| 1751051         | 0.9         | 3.4         | 0.8         | 0.76        | 0.47        | 0.77        |
| 1751052         | 1.5         | 6.8         | 1.6         | 1.77        | 0.94        | 1.94        |
| 1751053         | 0.7         | 4.1         | 0.9         | 1.13        | 0.53        | 1.11        |
| 1751054         | 1.2         | 3.2         | 0.7         | 0.83        | 0.42        | 0.94        |
| 1751055         | 1.3         | 3.3         | 0.7         | 1.02        | 0.41        | 0.83        |
| 1751056         | 1.3         | 3.5         | 0.8         | 0.99        | 0.47        | 0.83        |
| *Dup 1751039    | 0.9         | 4.5         | 0.9         | 0.82        | 0.64        | 0.68        |
| *Rep 1751053    | 0.7         | 4.3         | 0.9         | 1.18        | 0.55        | 1.14        |
| *Std OREAS 905  | 2.5         | 16.6        | 0.7         | 3.69        | 1.13        | 1.40        |
| *Blk BLANK      | <0.1        | <0.1        | <0.1        | <0.05       | <0.05       | <0.05       |
| *Blk BLANK      | <0.1        | <0.1        | <0.1        | <0.05       | <0.05       | <0.05       |
| *Std OREAS 601b | 6.2         | 11.7        | 0.5         | 2.75        | 0.91        | 1.02        |
| *Std OREAS 601b | 6.4         | 12.1        | 0.5         | 2.70        | 0.91        | 0.99        |

- not analysed | -- element not determined | I.S. insufficient sample | L.N.R. listed not received



Order Number PANCON\_RESOURCES  
 Project The Brewer Gold Project  
 Submission Number \*SD\* Pancon/ Brewer Gold B21C-  
 009/ 111 Core (1-56)  
 Number of Samples 56

## ANALYSIS REPORT BBM21-09948

| Element            | @W          | @Y          | @Yb         | Dy          | Er          | Eu          |
|--------------------|-------------|-------------|-------------|-------------|-------------|-------------|
| <b>Method</b>      | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 |
| <b>Lower Limit</b> | 0.1         | 0.1         | 0.1         | 0.05        | 0.05        | 0.05        |
| <b>Upper Limit</b> | 10,000      | 10,000      | 1,000       | 1,000       | 1,000       | 500         |
| <b>Unit</b>        | ppm m / m   | ppm m / m   | ppm m / m   | mg / kg     | mg / kg     | mg / kg     |
| *Std OREAS 905     | 2.9         | 17.3        | 0.7         | 3.94        | 1.29        | 1.52        |
| *Blk BLANK         | <0.1        | <0.1        | <0.1        | <0.05       | <0.05       | <0.05       |
| *Rep 1751038       | 0.7         | 4.6         | 0.9         | 0.83        | 0.65        | 0.60        |

| Element            | Gd          | Ho          | Nd          | Pr          | Sm          | Tm          |
|--------------------|-------------|-------------|-------------|-------------|-------------|-------------|
| <b>Method</b>      | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 |
| <b>Lower Limit</b> | 0.1         | 0.05        | 0.1         | 0.05        | 0.1         | 0.05        |
| <b>Upper Limit</b> | 1,000       | 500         | 1,000       | 1,000       | 1,000       | 500         |
| <b>Unit</b>        | mg / kg     | mg / kg     | mg / kg     | mg / kg     | mg / kg     | mg / kg     |
| 1751001            | 2.0         | 0.19        | 18.0        | 4.97        | 2.9         | 0.13        |
| 1751002            | 2.3         | 0.21        | 21.5        | 6.03        | 3.6         | 0.15        |
| 1751003            | 1.9         | 0.17        | 17.9        | 5.05        | 3.0         | 0.11        |
| 1751004            | 2.3         | 0.19        | 21.8        | 5.89        | 3.7         | 0.13        |
| 1751005            | 3.1         | 0.23        | 27.5        | 7.64        | 4.7         | 0.15        |
| 1751006            | 0.7         | 0.16        | 4.2         | 1.25        | 0.8         | 0.13        |
| 1751007            | 1.3         | 0.20        | 10.1        | 2.91        | 1.8         | 0.15        |
| 1751008            | 3.0         | 0.20        | 16.7        | 4.73        | 3.2         | 0.13        |
| 1751009            | 0.8         | 0.10        | 5.2         | 1.48        | 0.9         | 0.07        |
| 1751011            | 1.3         | 0.16        | 9.7         | 2.90        | 1.7         | 0.12        |
| 1751012            | 1.6         | 0.16        | 13.6        | 4.03        | 2.4         | 0.11        |
| 1751013            | 1.9         | 0.18        | 17.4        | 5.12        | 2.9         | 0.13        |
| 1751014            | 2.8         | 0.20        | 25.1        | 7.49        | 4.1         | 0.14        |
| 1751015            | 2.6         | 0.22        | 22.2        | 6.57        | 3.6         | 0.14        |
| 1751016            | 2.3         | 0.23        | 22.9        | 6.50        | 3.8         | 0.15        |
| 1751017            | 2.2         | 0.23        | 19.6        | 5.45        | 3.3         | 0.16        |
| 1751018            | 2.5         | 0.22        | 25.0        | 7.21        | 4.0         | 0.15        |
| 1751019            | 2.3         | 0.22        | 19.2        | 5.18        | 3.4         | 0.15        |
| 1751021            | 2.0         | 0.21        | 17.4        | 4.70        | 3.0         | 0.14        |

- not analysed | -- element not determined | I.S. insufficient sample | L.N.R. listed not received



Order Number PANCON\_RESOURCES  
 Project The Brewer Gold Project  
 Submission Number \*SD\* Pancon/ Brewer Gold B21C-  
 009/ 111 Core (1-56)  
 Number of Samples 56

**ANALYSIS REPORT BBM21-09948**

| Element     | Gd          | Ho          | Nd          | Pr          | Sm          | Tm          |
|-------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Method      | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 |
| Lower Limit | 0.1         | 0.05        | 0.1         | 0.05        | 0.1         | 0.05        |
| Upper Limit | 1,000       | 500         | 1,000       | 1,000       | 1,000       | 500         |
| Unit        | mg / kg     | mg / kg     | mg / kg     | mg / kg     | mg / kg     | mg / kg     |
| 1751022     | 1.9         | 0.20        | 18.4        | 5.09        | 3.1         | 0.14        |
| 1751023     | 1.2         | 0.11        | 8.9         | 2.46        | 1.7         | 0.07        |
| 1751024     | 2.2         | 0.22        | 18.6        | 5.13        | 3.5         | 0.15        |
| 1751025     | 1.8         | 0.20        | 18.6        | 5.20        | 3.0         | 0.14        |
| 1751026     | 1.8         | 0.18        | 18.5        | 5.15        | 3.0         | 0.14        |
| 1751027     | 2.4         | 0.15        | 25.7        | 7.35        | 4.3         | 0.10        |
| 1751028     | 2.1         | 0.17        | 22.0        | 6.14        | 3.8         | 0.13        |
| 1751029     | 2.2         | 0.15        | 24.1        | 6.72        | 4.1         | 0.10        |
| 1751031     | 2.1         | 0.10        | 25.2        | 7.17        | 4.0         | 0.06        |
| 1751032     | 2.1         | 0.17        | 20.9        | 5.79        | 3.7         | 0.12        |
| 1751033     | 2.3         | 0.16        | 23.7        | 6.80        | 3.9         | 0.11        |
| 1751034     | 1.8         | 0.09        | 21.0        | 6.19        | 3.3         | 0.06        |
| 1751035     | 2.4         | 0.15        | 23.6        | 6.79        | 3.9         | 0.10        |
| 1751036     | 2.5         | 0.17        | 26.3        | 6.98        | 4.3         | 0.11        |
| 1751037     | 2.0         | 0.15        | 18.4        | 5.25        | 3.2         | 0.10        |
| 1751038     | 1.7         | 0.16        | 16.0        | 4.61        | 2.7         | 0.11        |
| 1751039     | 1.9         | 0.17        | 18.9        | 5.26        | 3.2         | 0.11        |
| 1751041     | 1.9         | 0.16        | 20.4        | 5.89        | 3.2         | 0.11        |
| 1751042     | 2.2         | 0.16        | 27.2        | 7.88        | 4.2         | 0.11        |
| 1751043     | 2.7         | 0.19        | 34.8        | 9.84        | 5.3         | 0.12        |
| 1751044     | 2.1         | 0.15        | 25.8        | 7.65        | 3.9         | 0.10        |
| 1751045     | 1.9         | 0.15        | 21.5        | 6.26        | 3.2         | 0.10        |
| 1751046     | 0.7         | 0.07        | 5.4         | 1.58        | 0.9         | 0.06        |
| 1751047     | 1.2         | 0.12        | 11.6        | 3.46        | 1.9         | 0.10        |
| 1751048     | 2.0         | 0.12        | 23.0        | 6.73        | 3.6         | 0.08        |
| 1751049     | 3.5         | 0.16        | 36.4        | 10.87       | 5.6         | 0.08        |
| 1751051     | 2.0         | 0.14        | 21.5        | 6.40        | 3.5         | 0.09        |
| 1751052     | 5.0         | 0.30        | 53.1        | 15.25       | 8.3         | 0.19        |
| 1751053     | 3.1         | 0.18        | 30.3        | 8.89        | 4.8         | 0.10        |

- not analysed | -- element not determined | I.S. insufficient sample | L.N.R. listed not received





Order Number PANCON\_RESOURCES  
 Project The Brewer Gold Project  
 Submission Number \*SD\* Pancon/ Brewer Gold B21C-  
 009/ 111 Core (1-56)  
 Number of Samples 56

**ANALYSIS REPORT BBM21-09948**

| Element         | Gd          | Ho          | Nd          | Pr          | Sm          | Tm          |
|-----------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Method          | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 |
| Lower Limit     | 0.1         | 0.05        | 0.1         | 0.05        | 0.1         | 0.05        |
| Upper Limit     | 1,000       | 500         | 1,000       | 1,000       | 1,000       | 500         |
| Unit            | mg / kg     | mg / kg     | mg / kg     | mg / kg     | mg / kg     | mg / kg     |
| 1751054         | 2.5         | 0.13        | 25.4        | 7.58        | 4.1         | 0.08        |
| 1751055         | 2.4         | 0.14        | 22.0        | 6.72        | 3.5         | 0.08        |
| 1751056         | 2.4         | 0.15        | 22.7        | 6.94        | 3.4         | 0.09        |
| *Dup 1751039    | 1.9         | 0.17        | 19.3        | 5.44        | 3.2         | 0.11        |
| *Rep 1751053    | 3.1         | 0.19        | 30.7        | 9.21        | 4.8         | 0.10        |
| *Std OREAS 905  | 5.9         | 0.57        | 39.6        | 10.75       | 7.7         | 0.13        |
| *Blk BLANK      | <0.1        | <0.05       | <0.1        | <0.05       | <0.1        | <0.05       |
| *Blk BLANK      | <0.1        | <0.05       | <0.1        | <0.05       | <0.1        | <0.05       |
| *Std OREAS 601b | 4.4         | 0.41        | 30.8        | 8.45        | 5.8         | 0.10        |
| *Std OREAS 601b | 4.2         | 0.37        | 30.3        | 8.46        | 5.6         | 0.10        |
| *Std OREAS 905  | 6.2         | 0.53        | 41.9        | 11.42       | 8.2         | 0.14        |
| *Blk BLANK      | <0.1        | <0.05       | <0.1        | <0.05       | <0.1        | <0.05       |
| *Rep 1751038    | 1.6         | 0.16        | 15.5        | 4.48        | 2.7         | 0.11        |

SGS Canada Minerals Burnaby conforms to the requirements of ISO/IEC17025 for specific tests as listed on their scope of accreditation found at <https://www.scc.ca/en/search/laboratories/sgs>  
 Tests and Elements marked with an "@" symbol in the report denote ISO/IEC17025 accreditation.

- not analysed | -- element not determined | I.S. insufficient sample | L.N.R. listed not received



## ANALYSIS REPORT BBM21-09950

To COD SGS MINERALS - GEOCHEM VANCOUVER  
PANCON RESOURCES CAROLINAS CORP – JEN SPOHN  
201 ROUTE 17 NORTH, 7TH FLOOR  
Rutherford 07070  
Bergen  
UNITED STATES

|                   |                                    |                  |                           |
|-------------------|------------------------------------|------------------|---------------------------|
| Order Number      | PANCON_RESOURCES                   | Date Received    | 27-May-2021               |
| Project           | The Brewer Gold Project            | Date Analysed    | 15-Jun-2021 - 14-Jul-2021 |
| Submission Number | *SD* Pancon/ Brewer Gold B21C-009/ | Date Completed   | 15-Jul-2021               |
| 111 Core (57-111) |                                    | SGS Order Number | BBM21-09950               |
| Number of Samples | 55                                 |                  |                           |

### Methods Summary

| Number of Sample | Method Code | Description  |
|------------------|-------------|--|
| 55               | G_WGH_KG    | Weight of samples received                                   |
| 50               | G_PRP       | Combined Sample Preparation                                  |
| 55               | GE_FAA30V5  | Au, FAS, exploration grade, AAS, 30g-5ml                     |
| 49               | GE_DIG40Q12 | 4 Acid Digest (HCL/HCLO4/HF/HNO3)                            |
| 49               | GE_ICP40Q12 | 4 Acid Digest (HCL/HCLO4/HF/HNO3), ICP, 0.2g-12ml            |
| 49               | GE_IMS40Q12 | 4 Acid Digest Package (HCL/HCLO4/HF/HNO3), ICP-MS, 0.2g-12ml |
| 15               | GE_CSA06V   | Total Sulphur and Carbon, IR Combustion                      |

### Comments

Preparation of samples was performed at the SGS Sudbury site.

Analysis of samples was performed at the SGS Burnaby site.

Authorised Signatory

John Chiang  
Laboratory Operations  
Manager

This document is issued by the Company under its General Conditions of Service accessible at <https://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

**WARNING:** The sample(s) to which the findings recorded herein (the "Findings") relate was(were) drawn and / or provided by the Client or by a third party acting at the Client's direction. The Findings constitute no warranty of the sample's representativeness of any goods and strictly relate to the sample(s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted. The findings report on the samples provided by the client and are not intended for commercial or contractual settlement purposes.

- not analysed | -- element not determined | I.S. insufficient sample | L.N.R. listed not received



Order Number PANCON\_RESOURCES  
 Project The Brewer Gold Project  
 Submission Number \*SD\* Pancon/ Brewer Gold B21C-  
 009/ 111 Core (57-111)  
 Number of Samples 55

**ANALYSIS REPORT BBM21-09950**

| Element Method | WTG<br>G_WGH_KG | @Au<br>GE_FAA30V5 | @Al<br>GE_ICP40Q12 | @Ba<br>GE_ICP40Q12 | @Ca<br>GE_ICP40Q12 | @Cr<br>GE_ICP40Q12 |
|----------------|-----------------|-------------------|--------------------|--------------------|--------------------|--------------------|
| Lower Limit    | 0.01            | 5                 | 0.01               | 1                  | 0.01               | 1                  |
| Upper Limit    | --              | 10,000            | 15                 | 10,000             | 15                 | 10,000             |
| Unit           | kg              | ppb               | %                  | ppm m / m          | %                  | ppm m / m          |
| 1751057        | 6.07            | 110               | 7.19               | 48                 | 0.06               | 11                 |
| 1751058        | 5.91            | 141               | 8.01               | 131                | 0.07               | 13                 |
| 1751059        | 5.74            | 85                | 9.08               | 161                | 0.06               | 13                 |
| 1751060        | -               | 102               | -                  | -                  | -                  | -                  |
| 1751061        | 6.57            | 11                | 11.12              | 137                | 0.05               | 7                  |
| 1751062        | 6.28            | 30                | 11.78              | 77                 | 0.03               | 9                  |
| 1751063        | 6.24            | 37                | 12.34              | 127                | 0.04               | 6                  |
| 1751064        | 6.32            | 58                | 9.88               | 410                | 0.03               | 10                 |
| 1751065        | 6.47            | 52                | 11.17              | 850                | 0.03               | 8                  |
| 1751066        | 5.57            | 52                | 10.92              | 443                | 0.03               | 9                  |
| 1751067        | 6.51            | 213               | 9.58               | 306                | 0.04               | 7                  |
| 1751068        | 5.85            | 81                | 7.00               | 155                | 0.05               | 9                  |
| 1751069        | 4.32            | 84                | 6.92               | 152                | 0.03               | 7                  |
| 1751070        | 0.05            | 684               | -                  | -                  | -                  | -                  |
| 1751071        | 3.87            | 229               | 5.92               | 91                 | 0.05               | 7                  |
| 1751072        | 6.13            | 160               | 5.57               | 237                | 0.05               | 8                  |
| 1751073        | 6.56            | 275               | 1.46               | 35                 | 0.04               | 8                  |
| 1751074        | 3.93            | 270               | 1.54               | 28                 | 0.01               | 7                  |
| 1751075        | 3.99            | 224               | 1.56               | 65                 | 0.03               | 6                  |
| 1751076        | 6.87            | 97                | 8.33               | 70                 | 0.02               | 6                  |
| 1751077        | 5.94            | 34                | 6.35               | 54                 | 0.01               | 5                  |
| 1751078        | 4.34            | 74                | 7.97               | 96                 | 0.02               | 7                  |
| 1751079        | 6.17            | 1020              | 1.03               | 17                 | 0.01               | 8                  |
| 1751080        | 2.14            | <5                | -                  | -                  | -                  | -                  |
| 1751081        | 5.14            | 599               | 3.18               | 142                | 0.01               | 7                  |
| 1751082        | 2.82            | 11                | 0.87               | 7                  | <0.01              | 9                  |
| 1751083        | 6.11            | 399               | 7.54               | 121                | 0.01               | 16                 |
| 1751084        | 5.49            | 431               | 7.40               | 70                 | 0.01               | 6                  |
| 1751085        | 4.30            | 1150              | 8.47               | 234                | 0.03               | 15                 |

- not analysed | -- element not determined | I.S. insufficient sample | L.N.R. listed not received



Order Number PANCON\_RESOURCES  
 Project The Brewer Gold Project  
 Submission Number \*SD\* Pancon/ Brewer Gold B21C-  
 009/ 111 Core (57-111)  
 Number of Samples 55

**ANALYSIS REPORT BBM21-09950**

| Element<br>Method<br>Lower Limit<br>Upper Limit<br>Unit | WTG<br>G_WGH_KG<br>0.01<br>--<br>kg | @Au<br>GE_FAA30V5<br>5<br>10,000<br>ppb | @Al<br>GE_ICP40Q12<br>0.01<br>15<br>% | @Ba<br>GE_ICP40Q12<br>1<br>10,000<br>ppm m / m | @Ca<br>GE_ICP40Q12<br>0.01<br>15<br>% | @Cr<br>GE_ICP40Q12<br>1<br>10,000<br>ppm m / m |
|---|-------------------------------------|---|---------------------------------------|--|---------------------------------------|--|
| 1751086   | 3.18                                | 125                                     | 0.67                                  | 9  | <0.01                                 | 18   |
| 1751087   | 6.17                                | 3980                                    | 2.05                                  | 27   | <0.01                                 | 15   |
| 1751088   | 6.23                                | 2400                                    | 8.49                                  | 115  | <0.01                                 | 11   |
| 1751089   | 5.58                                | 788                                     | 6.39                                  | 72   | 0.02                                  | 13   |
| 1751090   | -                                   | 969                                     | -                                     | -  | -                                     | -  |
| 1751091   | 5.80                                | 442                                     | 3.09                                  | 258  | 0.02                                  | 9  |
| 1751092   | 6.79                                | 750                                     | 7.90                                  | 180  | 0.03                                  | 13   |
| 1751093   | 6.12                                | 111                                     | 4.08                                  | 219  | 0.04                                  | 11   |
| 1751094   | 6.19                                | 21                                      | 6.81                                  | 253  | 0.02                                  | 7  |
| 1751095   | 6.06                                | 513                                     | 6.00                                  | 426  | 0.03                                  | 15   |
| 1751096   | 4.90                                | 117                                     | 1.22                                  | 176  | 0.01                                  | 10   |
| 1751097   | 5.93                                | 86                                      | 4.32                                  | 146  | <0.01                                 | 10   |
| 1751098   | 6.39                                | 70                                      | 7.69                                  | 259  | 0.02                                  | 10   |
| 1751099   | 4.31                                | 110                                     | 4.86                                  | 94   | 0.02                                  | 10   |
| 1751100   | 0.05                                | 1910                                    | -                                     | -  | -                                     | -  |
| 1751101   | 4.98                                | 149                                     | 6.58                                  | 88   | 0.01                                  | 6  |
| 1751102   | 4.58                                | 94                                      | 7.42                                  | 90   | 0.04                                  | 10   |
| 1751103   | 6.14                                | 235                                     | 9.24                                  | 139  | 0.05                                  | 7  |
| 1751104   | 5.72                                | 154                                     | 10.99                                 | 126  | 0.06                                  | 4  |
| 1751105   | 5.87                                | 259                                     | 8.44                                  | 238  | 0.02                                  | 4  |
| 1751106   | 6.25                                | 235                                     | 10.10                                 | 133  | 0.04                                  | 4  |
| 1751107   | 6.15                                | 201                                     | 5.30                                  | 133  | 0.03                                  | 5  |
| 1751108   | 5.33                                | 82                                      | 5.81                                  | 557  | 0.03                                  | 7  |
| 1751109   | 3.92                                | 141                                     | 6.12                                  | 229  | 0.03                                  | 7  |
| 1751110   | 0.05                                | <5                                      | -                                     | -  | -                                     | -  |
| 1751111   | 5.09                                | 346                                     | 6.68                                  | 179  | 0.04                                  | 5  |
| *Dup 1751095  | -                                   | 560                                     | 5.66                                  | 624  | 0.03                                  | 11   |
| *Std OREAS 279  | -                                   | 6480                                    | -                                     | -  | -                                     | -  |
| *Blk BLANK  | -                                   | <5                                      | -                                     | -  | -                                     | -  |

- not analysed | -- element not determined | I.S. insufficient sample | L.N.R. listed not received



Order Number PANCON\_RESOURCES  
 Project The Brewer Gold Project  
 Submission Number \*SD\* Pancon/ Brewer Gold B21C-  
 009/ 111 Core (57-111)  
 Number of Samples 55

## ANALYSIS REPORT BBM21-09950

| Element Method  | WTG<br>G_WGH_KG | @Au<br>GE_FAA30V5 | @Al<br>GE_ICP40Q12 | @Ba<br>GE_ICP40Q12 | @Ca<br>GE_ICP40Q12 | @Cr<br>GE_ICP40Q12 |
|-----------------|-----------------|-------------------|--------------------|--------------------|--------------------|--------------------|
| Lower Limit     | 0.01            | 5                 | 0.01               | 1                  | 0.01               | 1                  |
| Upper Limit     | --              | 10,000            | 15                 | 10,000             | 15                 | 10,000             |
| Unit            | kg              | ppb               | %                  | ppm m / m          | %                  | ppm m / m          |
| *Std GS-9B      | -               | 8690              | -                  | -                  | -                  | -                  |
| *Std OREAS 235  | -               | 1590              | -                  | -                  | -                  | -                  |
| *Blk BLANK      | -               | <5                | -                  | -                  | -                  | -                  |
| *Rep 1751061    | -               | 14                | -                  | -                  | -                  | -                  |
| *Blk BLANK      | -               | 5                 | -                  | -                  | -                  | -                  |
| *Rep 1751076    | -               | 95                | -                  | -                  | -                  | -                  |
| *Rep 1751105    | -               | 268               | -                  | -                  | -                  | -                  |
| *Std OREAS 279  | -               | 6960              | -                  | -                  | -                  | -                  |
| *Std GS-9B      | -               | 8260              | -                  | -                  | -                  | -                  |
| *Std OREAS 235  | -               | 1700              | -                  | -                  | -                  | -                  |
| *Blk BLANK      | -               | <5                | -                  | -                  | -                  | -                  |
| *Std OREAS 905  | -               | -                 | 7.34               | 2699               | 0.57               | 12                 |
| *Blk BLANK      | -               | -                 | <0.01              | <1                 | <0.01              | <1                 |
| *Blk BLANK      | -               | -                 | 0.01               | <1                 | <0.01              | <1                 |
| *Std OREAS 601b | -               | -                 | 6.33               | 853                | 0.82               | 17                 |
| *Std OREAS 905  | -               | -                 | 7.35               | 2588               | 0.55               | 13                 |
| *Std OREAS 601b | -               | -                 | 6.48               | 873                | 0.83               | 19                 |
| *Blk BLANK      | -               | -                 | <0.01              | 2                  | <0.01              | <1                 |
| *Rep 1751109    | -               | -                 | 6.13               | 195                | 0.03               | 9                  |

| Element Method | @Cu<br>GE_ICP40Q12 | @Fe<br>GE_ICP40Q12 | @K<br>GE_ICP40Q12 | @Li<br>GE_ICP40Q12 | @Mg<br>GE_ICP40Q12 | @Mn<br>GE_ICP40Q12 |
|----------------|--------------------|--------------------|-------------------|--------------------|--------------------|--------------------|
| Lower Limit    | 0.5                | 0.01               | 0.01              | 1                  | 0.01               | 2                  |
| Upper Limit    | 10,000             | 15                 | 15                | 10,000             | 15                 | 10,000             |
| Unit           | ppm m / m          | %                  | %                 | ppm m / m          | %                  | ppm m / m          |
| 1751057        | 224                | 1.71               | 0.04              | <1                 | <0.01              | 33                 |
| 1751058        | 194                | 1.98               | 0.04              | <1                 | 0.01               | 42                 |
| 1751059        | 85.8               | 1.42               | 0.04              | <1                 | <0.01              | 31                 |

- not analysed | -- element not determined | I.S. insufficient sample | L.N.R. listed not received



Order Number PANCON\_RESOURCES  
 Project The Brewer Gold Project  
 Submission Number \*SD\* Pancon/ Brewer Gold B21C-  
 009/ 111 Core (57-111)  
 Number of Samples 55

## ANALYSIS REPORT BBM21-09950

| Element     | @Cu         | @Fe         | @K          | @Li         | @Mg         | @Mn         |
|-------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Method      | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 |
| Lower Limit | 0.5         | 0.01        | 0.01        | 1           | 0.01        | 2           |
| Upper Limit | 10,000      | 15          | 15          | 10,000      | 15          | 10,000      |
| Unit        | ppm m / m   | %           | %           | ppm m / m   | %           | ppm m / m   |
| 1751060     | -           | -           | -           | -           | -           | -           |
| 1751061     | 37.0        | 0.46        | 0.07        | <1          | <0.01       | 28          |
| 1751062     | 54.4        | 1.15        | 0.04        | <1          | <0.01       | 53          |
| 1751063     | 64.1        | 1.17        | 0.07        | 4           | <0.01       | 25          |
| 1751064     | 95.6        | 2.24        | 0.05        | <1          | <0.01       | 41          |
| 1751065     | 91.2        | 1.92        | 0.08        | <1          | <0.01       | 27          |
| 1751066     | 90.6        | 2.19        | 0.05        | <1          | <0.01       | 42          |
| 1751067     | 664         | 3.12        | 0.05        | <1          | <0.01       | 28          |
| 1751068     | 233         | 4.61        | 0.02        | <1          | <0.01       | 46          |
| 1751069     | 249         | 4.81        | 0.04        | <1          | <0.01       | 27          |
| 1751070     | -           | -           | -           | -           | -           | -           |
| 1751071     | 267         | 5.40        | 0.02        | <1          | <0.01       | 31          |
| 1751072     | 265         | 6.02        | 0.02        | <1          | <0.01       | 34          |
| 1751073     | 397         | 6.88        | 0.02        | <1          | <0.01       | 42          |
| 1751074     | 146         | 6.82        | 0.01        | <1          | <0.01       | 50          |
| 1751075     | 99.7        | 8.86        | 0.01        | <1          | <0.01       | 41          |
| 1751076     | 167         | 1.62        | 0.02        | <1          | <0.01       | 42          |
| 1751077     | 38.5        | 1.22        | 0.01        | <1          | <0.01       | 36          |
| 1751078     | 176         | 1.72        | 0.02        | <1          | <0.01       | 35          |
| 1751079     | 1115        | 12.94       | 0.01        | <1          | <0.01       | 34          |
| 1751080     | -           | -           | -           | -           | -           | -           |
| 1751081     | 1538        | 4.20        | 0.01        | <1          | <0.01       | 34          |
| 1751082     | 19.6        | 0.85        | <0.01       | <1          | <0.01       | 61          |
| 1751083     | 790         | 1.62        | 0.03        | 1           | <0.01       | 31          |
| 1751084     | 1076        | 0.80        | 0.02        | 1           | <0.01       | 32          |
| 1751085     | 5056        | 2.60        | 0.02        | 1           | <0.01       | 24          |
| 1751086     | 563         | 0.81        | <0.01       | <1          | <0.01       | 69          |
| 1751087     | 5429        | 2.61        | 0.01        | <1          | <0.01       | 40          |
| 1751088     | 6026        | 3.88        | 0.03        | <1          | <0.01       | 36          |

- not analysed | -- element not determined | I.S. insufficient sample | L.N.R. listed not received



Order Number PANCON\_RESOURCES  
 Project The Brewer Gold Project  
 Submission Number \*SD\* Pancon/ Brewer Gold B21C-  
 009/ 111 Core (57-111)  
 Number of Samples 55

## ANALYSIS REPORT BBM21-09950

| Element         | @Cu         | @Fe         | @K          | @Li         | @Mg         | @Mn         |
|-----------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Method          | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 |
| Lower Limit     | 0.5         | 0.01        | 0.01        | 1           | 0.01        | 2           |
| Upper Limit     | 10,000      | 15          | 15          | 10,000      | 15          | 10,000      |
| Unit            | ppm m / m   | %           | %           | ppm m / m   | %           | ppm m / m   |
| 1751089         | 2310        | 5.96        | 0.05        | <1          | <0.01       | 36          |
| 1751090         | -           | -           | -           | -           | -           | -           |
| 1751091         | 913         | 2.84        | 0.02        | <1          | <0.01       | 38          |
| 1751092         | 876         | 3.85        | 0.05        | <1          | <0.01       | 42          |
| 1751093         | 66.6        | 3.75        | 0.06        | <1          | <0.01       | 37          |
| 1751094         | 31.1        | 0.86        | 0.10        | <1          | <0.01       | 38          |
| 1751095         | 318         | 2.06        | 0.13        | <1          | <0.01       | 37          |
| 1751096         | 81.7        | 3.30        | 0.21        | <1          | <0.01       | 36          |
| 1751097         | 43.3        | 2.32        | 0.30        | <1          | <0.01       | 36          |
| 1751098         | 52.3        | 2.36        | 0.31        | <1          | <0.01       | 36          |
| 1751099         | 47.3        | 4.78        | 0.13        | <1          | <0.01       | 40          |
| 1751100         | -           | -           | -           | -           | -           | -           |
| 1751101         | 43.3        | 6.35        | 0.16        | <1          | <0.01       | 31          |
| 1751102         | 157         | 5.80        | 1.49        | <1          | 0.01        | 30          |
| 1751103         | 128         | 5.55        | 1.77        | 1           | 0.01        | 23          |
| 1751104         | 110         | 5.88        | 2.79        | <1          | 0.02        | 22          |
| 1751105         | 43.7        | 2.74        | 2.52        | <1          | 0.01        | 31          |
| 1751106         | 95.9        | 4.76        | 3.34        | <1          | 0.02        | 24          |
| 1751107         | 99.8        | 3.43        | 1.64        | <1          | <0.01       | 27          |
| 1751108         | 38.5        | 1.15        | 1.52        | <1          | <0.01       | 32          |
| 1751109         | 25.0        | 1.07        | 1.40        | <1          | <0.01       | 35          |
| 1751110         | -           | -           | -           | -           | -           | -           |
| 1751111         | 139         | 4.70        | 1.79        | <1          | <0.01       | 28          |
| *Dup 1751095    | 273         | 2.00        | 0.11        | <1          | <0.01       | 40          |
| *Std OREAS 905  | 1488        | 3.84        | 2.93        | 20          | 0.28        | 357         |
| *Blk BLANK      | <0.5        | <0.01       | <0.01       | <1          | <0.01       | <2          |
| *Blk BLANK      | <0.5        | <0.01       | <0.01       | <1          | <0.01       | <2          |
| *Std OREAS 601b | 967         | 2.29        | 2.37        | 22          | 0.09        | 222         |
| *Std OREAS 905  | 1479        | 3.94        | 2.97        | 20          | 0.27        | 360         |

- not analysed | -- element not determined | I.S. insufficient sample | L.N.R. listed not received



Order Number PANCON\_RESOURCES  
 Project The Brewer Gold Project  
 Submission Number \*SD\* Pancon/ Brewer Gold B21C-  
 009/ 111 Core (57-111)  
 Number of Samples 55

## ANALYSIS REPORT BBM21-09950

| Element         | @Cu         | @Fe         | @K          | @Li         | @Mg         | @Mn         |
|-----------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Method          | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 |
| Lower Limit     | 0.5         | 0.01        | 0.01        | 1           | 0.01        | 2           |
| Upper Limit     | 10,000      | 15          | 15          | 10,000      | 15          | 10,000      |
| Unit            | ppm m / m   | %           | %           | ppm m / m   | %           | ppm m / m   |
| *Std OREAS 601b | 968         | 2.17        | 2.44        | 23          | 0.09        | 211         |
| *Blk BLANK      | 1.0         | 0.01        | <0.01       | <1          | <0.01       | <2          |
| *Rep 1751109    | 25.6        | 1.09        | 1.39        | <1          | <0.01       | 35          |

| Element     | @Na         | @Ni         | @P          | @S          | @Sr         | @Ti         |
|-------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Method      | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 |
| Lower Limit | 0.01        | 1           | 0.01        | 0.01        | 0.5         | 0.01        |
| Upper Limit | 15          | 10,000      | 15          | 5           | 10,000      | 15          |
| Unit        | %           | ppm m / m   | %           | %           | ppm m / m   | %           |
| 1751057     | 0.02        | 4           | 0.11        | 1.70        | 179         | 0.06        |
| 1751058     | 0.02        | 4           | 0.13        | 1.91        | 330         | 0.08        |
| 1751059     | 0.02        | 3           | 0.11        | 1.37        | 331         | 0.07        |
| 1751060     | -           | -           | -           | -           | -           | -           |
| 1751061     | 0.02        | 1           | 0.09        | 0.29        | 413         | 0.05        |
| 1751062     | 0.02        | 3           | 0.06        | 0.83        | 273         | 0.05        |
| 1751063     | 0.06        | 5           | 0.09        | 1.14        | 228         | 0.06        |
| 1751064     | 0.02        | 5           | 0.07        | 2.27        | 313         | 0.05        |
| 1751065     | 0.02        | 4           | 0.09        | 2.03        | 325         | 0.07        |
| 1751066     | 0.02        | 5           | 0.08        | 2.21        | 410         | 0.06        |
| 1751067     | 0.02        | 8           | 0.09        | 3.68        | 392         | 0.06        |
| 1751068     | 0.02        | 9           | 0.10        | >5.00       | 274         | 0.07        |
| 1751069     | 0.02        | 10          | 0.08        | >5.00       | 222         | 0.06        |
| 1751070     | -           | -           | -           | -           | -           | -           |
| 1751071     | 0.01        | 11          | 0.11        | >5.00       | 337         | 0.05        |
| 1751072     | 0.01        | 11          | 0.11        | >5.00       | 336         | 0.05        |
| 1751073     | 0.01        | 13          | 0.06        | >5.00       | 210         | 0.04        |
| 1751074     | <0.01       | 12          | 0.03        | >5.00       | 157         | 0.03        |
| 1751075     | 0.01        | 14          | 0.07        | >5.00       | 328         | 0.03        |

- not analysed | -- element not determined | I.S. insufficient sample | L.N.R. listed not received





Order Number PANCON\_RESOURCES  
 Project The Brewer Gold Project  
 Submission Number \*SD\* Pancon/ Brewer Gold B21C-  
 009/ 111 Core (57-111)  
 Number of Samples 55

## ANALYSIS REPORT BBM21-09950

| Element     | @Na         | @Ni         | @P          | @S          | @Sr         | @Ti         |
|-------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Method      | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 |
| Lower Limit | 0.01        | 1           | 0.01        | 0.01        | 0.5         | 0.01        |
| Upper Limit | 15          | 10,000      | 15          | 5           | 10,000      | 15          |
| Unit        | %           | ppm m / m   | %           | %           | ppm m / m   | %           |
| 1751076     | 0.01        | 7           | 0.05        | 1.50        | 200         | 0.05        |
| 1751077     | 0.01        | 3           | 0.03        | 1.04        | 167         | 0.06        |
| 1751078     | 0.02        | 6           | 0.05        | 1.76        | 366         | 0.08        |
| 1751079     | 0.01        | 46          | 0.02        | >5.00       | 133         | 0.05        |
| 1751080     | -           | -           | -           | -           | -           | -           |
| 1751081     | <0.01       | 17          | 0.02        | 4.22        | 92.0        | 0.06        |
| 1751082     | <0.01       | 2           | <0.01       | 0.30        | 5.7         | <0.01       |
| 1751083     | 0.02        | 8           | 0.03        | 1.61        | 171         | 0.07        |
| 1751084     | 0.02        | 3           | 0.03        | 0.60        | 278         | 0.05        |
| 1751085     | 0.02        | 14          | 0.06        | 2.87        | 368         | 0.09        |
| 1751086     | <0.01       | 2           | <0.01       | 0.18        | 5.8         | 0.01        |
| 1751087     | <0.01       | 10          | 0.01        | 2.69        | 96.7        | 0.08        |
| 1751088     | 0.02        | 19          | 0.02        | 4.16        | 172         | 0.05        |
| 1751089     | 0.02        | 41          | 0.06        | >5.00       | 335         | 0.04        |
| 1751090     | -           | -           | -           | -           | -           | -           |
| 1751091     | 0.01        | 17          | 0.06        | 2.99        | 286         | 0.06        |
| 1751092     | 0.02        | 14          | 0.08        | 3.88        | 244         | 0.06        |
| 1751093     | 0.03        | 8           | 0.06        | 3.82        | 98.4        | 0.05        |
| 1751094     | 0.02        | 2           | 0.04        | 0.53        | 161         | 0.07        |
| 1751095     | 0.03        | 5           | 0.09        | 1.93        | 198         | 0.06        |
| 1751096     | 0.03        | 7           | 0.02        | 3.24        | 32.0        | 0.05        |
| 1751097     | 0.03        | 4           | 0.02        | 2.25        | 80.7        | 0.06        |
| 1751098     | 0.04        | 4           | 0.05        | 2.35        | 113         | 0.07        |
| 1751099     | 0.02        | 7           | 0.05        | 4.90        | 333         | 0.04        |
| 1751100     | -           | -           | -           | -           | -           | -           |
| 1751101     | 0.03        | 8           | 0.03        | >5.00       | 59.9        | 0.03        |
| 1751102     | 0.16        | 7           | 0.06        | >5.00       | 349         | 0.02        |
| 1751103     | 0.18        | 6           | 0.08        | >5.00       | 431         | 0.04        |
| 1751104     | 0.27        | 7           | 0.08        | >5.00       | 374         | 0.04        |

- not analysed | -- element not determined | I.S. insufficient sample | L.N.R. listed not received



Order Number PANCON\_RESOURCES  
 Project The Brewer Gold Project  
 Submission Number \*SD\* Pancon/ Brewer Gold B21C-  
 009/ 111 Core (57-111)  
 Number of Samples 55

## ANALYSIS REPORT BBM21-09950

| Element         | @Na         | @Ni         | @P          | @S          | @Sr         | @Ti         |
|-----------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Method          | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 |
| Lower Limit     | 0.01        | 1           | 0.01        | 0.01        | 0.5         | 0.01        |
| Upper Limit     | 15          | 10,000      | 15          | 5           | 10,000      | 15          |
| Unit            | %           | ppm m / m   | %           | %           | ppm m / m   | %           |
| 1751105         | 0.24        | 3           | 0.03        | 2.81        | 184         | 0.04        |
| 1751106         | 0.35        | 5           | 0.07        | >5.00       | 417         | 0.04        |
| 1751107         | 0.24        | 4           | 0.05        | 3.72        | 329         | 0.04        |
| 1751108         | 0.55        | 2           | 0.05        | 2.49        | 304         | 0.06        |
| 1751109         | 0.75        | 1           | 0.05        | 3.14        | 319         | 0.07        |
| 1751110         | -           | -           | -           | -           | -           | -           |
| 1751111         | 0.32        | 5           | 0.06        | >5.00       | 442         | 0.04        |
| *Dup 1751095    | 0.02        | 5           | 0.08        | 1.86        | 172         | 0.06        |
| *Std OREAS 905  | 2.34        | 9           | 0.03        | 0.08        | 159         | 0.11        |
| *Blk BLANK      | <0.01       | <1          | <0.01       | <0.01       | <0.5        | <0.01       |
| *Blk BLANK      | <0.01       | <1          | <0.01       | <0.01       | <0.5        | <0.01       |
| *Std OREAS 601b | 1.88        | 6           | 0.03        | 1.45        | 242         | 0.12        |
| *Std OREAS 905  | 2.39        | 9           | 0.03        | 0.08        | 161         | 0.11        |
| *Std OREAS 601b | 1.87        | 6           | 0.03        | 1.44        | 245         | 0.13        |
| *Blk BLANK      | <0.01       | <1          | <0.01       | 0.02        | 1.1         | <0.01       |
| *Rep 1751109    | 0.75        | 2           | 0.05        | 3.19        | 316         | 0.06        |

| Element     | @V          | @Zn         | @Zr         | @Ag         | @As         | @Be         |
|-------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Method      | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 |
| Lower Limit | 2           | 1           | 0.5         | 0.02        | 1           | 0.1         |
| Upper Limit | 10,000      | 10,000      | 10,000      | 100         | 10,000      | 2,500       |
| Unit        | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   |
| 1751057     | 12          | <1          | 90.6        | 0.28        | 5           | <0.1        |
| 1751058     | 12          | 3           | 102         | 0.26        | 6           | <0.1        |
| 1751059     | 15          | 1           | 90.6        | 0.17        | 3           | <0.1        |
| 1751060     | -           | -           | -           | -           | -           | -           |
| 1751061     | 19          | 2           | 64.4        | 0.07        | 4           | 0.1         |
| 1751062     | 14          | 5           | 57.8        | 0.07        | 7           | <0.1        |

- not analysed | -- element not determined | I.S. insufficient sample | L.N.R. listed not received



Order Number PANCON\_RESOURCES  
 Project The Brewer Gold Project  
 Submission Number \*SD\* Pancon/ Brewer Gold B21C-  
 009/ 111 Core (57-111)  
 Number of Samples 55

## ANALYSIS REPORT BBM21-09950

| Element     | @V          | @Zn         | @Zr         | @Ag         | @As         | @Be         |
|-------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Method      | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 |
| Lower Limit | 2           | 1           | 0.5         | 0.02        | 1           | 0.1         |
| Upper Limit | 10,000      | 10,000      | 10,000      | 100         | 10,000      | 2,500       |
| Unit        | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   |
| 1751063     | 19          | 1           | 77.3        | <0.02       | 6           | 0.1         |
| 1751064     | 25          | 2           | 84.6        | 0.08        | 7           | 0.1         |
| 1751065     | 34          | <1          | 81.8        | 0.10        | 6           | <0.1        |
| 1751066     | 30          | 1           | 84.9        | 0.15        | 8           | 0.1         |
| 1751067     | 25          | <1          | 92.8        | 0.66        | 19          | 0.1         |
| 1751068     | 15          | 2           | 127         | 0.33        | 11          | <0.1        |
| 1751069     | 14          | 2           | 123         | 0.37        | 22          | <0.1        |
| 1751070     | -           | -           | -           | -           | -           | -           |
| 1751071     | 10          | <1          | 91.8        | 0.63        | 15          | 0.2         |
| 1751072     | 9           | 2           | 88.7        | 0.44        | 22          | <0.1        |
| 1751073     | 5           | <1          | 100         | 0.42        | 29          | <0.1        |
| 1751074     | 4           | <1          | 65.5        | 0.15        | 56          | <0.1        |
| 1751075     | 4           | <1          | 61.7        | 0.27        | 35          | <0.1        |
| 1751076     | 12          | 2           | 64.8        | 0.20        | 7           | <0.1        |
| 1751077     | 9           | <1          | 82.3        | 0.04        | 6           | <0.1        |
| 1751078     | 12          | 2           | 123         | 0.21        | 6           | <0.1        |
| 1751079     | 3           | <1          | 106         | 2.17        | 78          | <0.1        |
| 1751080     | -           | -           | -           | -           | -           | -           |
| 1751081     | 6           | <1          | 93.4        | 1.45        | 14          | <0.1        |
| 1751082     | 3           | <1          | 8.4         | 0.03        | 2           | <0.1        |
| 1751083     | 11          | <1          | 122         | 0.84        | 6           | <0.1        |
| 1751084     | 10          | <1          | 63.6        | 1.02        | 7           | <0.1        |
| 1751085     | 10          | <1          | 131         | 5.73        | 16          | <0.1        |
| 1751086     | 3           | <1          | 16.9        | 0.92        | 4           | <0.1        |
| 1751087     | 6           | <1          | 103         | 6.21        | 16          | <0.1        |
| 1751088     | 10          | <1          | 76.4        | 6.09        | 24          | <0.1        |
| 1751089     | 9           | <1          | 92.1        | 2.80        | 18          | <0.1        |
| 1751090     | -           | -           | -           | -           | -           | -           |
| 1751091     | 6           | <1          | 94.3        | 1.00        | 7           | <0.1        |

- not analysed | -- element not determined | I.S. insufficient sample | L.N.R. listed not received



Order Number PANCON\_RESOURCES  
 Project The Brewer Gold Project  
 Submission Number \*SD\* Pancon/ Brewer Gold B21C-  
 009/ 111 Core (57-111)  
 Number of Samples 55

## ANALYSIS REPORT BBM21-09950

| Element         | @V          | @Zn         | @Zr         | @Ag         | @As         | @Be         |
|-----------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Method          | GE_ICP40Q12 | GE_ICP40Q12 | GE_ICP40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 |
| Lower Limit     | 2           | 1           | 0.5         | 0.02        | 1           | 0.1         |
| Upper Limit     | 10,000      | 10,000      | 10,000      | 100         | 10,000      | 2,500       |
| Unit            | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   |
| 1751092         | 11          | <1          | 100         | 0.94        | 12          | <0.1        |
| 1751093         | 8           | <1          | 98.2        | 0.05        | 4           | <0.1        |
| 1751094         | 13          | <1          | 91.1        | 0.05        | 4           | <0.1        |
| 1751095         | 13          | <1          | 89.6        | 0.38        | 9           | <0.1        |
| 1751096         | 10          | <1          | 81.5        | 0.23        | 6           | <0.1        |
| 1751097         | 19          | <1          | 90.8        | 0.11        | 4           | <0.1        |
| 1751098         | 24          | <1          | 103         | <0.02       | 6           | <0.1        |
| 1751099         | 14          | <1          | 94.6        | 0.02        | 15          | <0.1        |
| 1751100         | -           | -           | -           | -           | -           | -           |
| 1751101         | 16          | <1          | 81.6        | 0.03        | 7           | <0.1        |
| 1751102         | 59          | <1          | 64.2        | 0.13        | 5           | <0.1        |
| 1751103         | 62          | <1          | 91.0        | 0.16        | 6           | 0.1         |
| 1751104         | 78          | <1          | 103         | 0.13        | 6           | 0.2         |
| 1751105         | 56          | <1          | 73.2        | 0.07        | 7           | 0.2         |
| 1751106         | 62          | <1          | 63.7        | 0.11        | 8           | 0.2         |
| 1751107         | 35          | <1          | 77.4        | 0.14        | 14          | 0.1         |
| 1751108         | 50          | <1          | 93.6        | <0.02       | 8           | <0.1        |
| 1751109         | 53          | <1          | 86.5        | <0.02       | 9           | <0.1        |
| 1751110         | -           | -           | -           | -           | -           | -           |
| 1751111         | 57          | <1          | 80.6        | 0.15        | 36          | 0.2         |
| *Dup 1751095    | 12          | <1          | 93.0        | 0.39        | 9           | <0.1        |
| *Std OREAS 905  | 9           | 135         | 245         | 0.64        | 35          | 2.7         |
| *Blk BLANK      | <2          | 1           | <0.5        | <0.02       | <1          | <0.1        |
| *Blk BLANK      | <2          | <1          | <0.5        | <0.02       | <1          | <0.1        |
| *Std OREAS 601b | 11          | 295         | 174         | 48.50       | 302         | 2.2         |
| *Std OREAS 905  | 9           | 135         | 245         | 0.47        | 37          | 2.6         |
| *Std OREAS 601b | 11          | 318         | 181         | 52.94       | 278         | 2.0         |
| *Blk BLANK      | <2          | 2           | 0.5         | 0.04        | <1          | <0.1        |
| *Rep 1751109    | 52          | <1          | 82.7        | <0.02       | 8           | <0.1        |

- not analysed | -- element not determined | I.S. insufficient sample | L.N.R. listed not received



Order Number PANCON\_RESOURCES  
 Project The Brewer Gold Project  
 Submission Number \*SD\* Pancon/ Brewer Gold B21C-  
 009/ 111 Core (57-111)  
 Number of Samples 55

## ANALYSIS REPORT BBM21-09950

| Element     | @Bi         | @Cd         | @Ce         | @Co         | @Cs         | @Ga         |
|-------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Method      | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 |
| Lower Limit | 0.04        | 0.02        | 0.05        | 0.1         | 1           | 0.1         |
| Upper Limit | 10,000      | 10,000      | 1,000       | 10,000      | 1,000       | 1,000       |
| Unit        | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   |
| 1751057     | 7.71        | 0.03        | 61.25       | 12.0        | <1          | 9.6         |
| 1751058     | 6.76        | 0.02        | 50.94       | 13.3        | <1          | 8.9         |
| 1751059     | 2.44        | <0.02       | 35.24       | 7.1         | <1          | 9.0         |
| 1751060     | -           | -           | -           | -           | -           | -           |
| 1751061     | 0.94        | <0.02       | 61.83       | 1.8         | <1          | 11.3        |
| 1751062     | 1.14        | 0.06        | 60.77       | 7.7         | <1          | 13.4        |
| 1751063     | 1.51        | <0.02       | 53.41       | 9.8         | <1          | 16.0        |
| 1751064     | 2.35        | <0.02       | 82.72       | 15.4        | <1          | 12.7        |
| 1751065     | 4.34        | <0.02       | 71.30       | 10.9        | <1          | 20.5        |
| 1751066     | 3.83        | 0.02        | 86.14       | 11.3        | <1          | 23.5        |
| 1751067     | 21.29       | 0.03        | 114         | 22.0        | <1          | 22.0        |
| 1751068     | 9.52        | 0.03        | 127         | 20.1        | <1          | 10.6        |
| 1751069     | 10.96       | 0.03        | 62.48       | 31.5        | <1          | 11.3        |
| 1751070     | -           | -           | -           | -           | -           | -           |
| 1751071     | 19.29       | 0.06        | 80.75       | 29.9        | <1          | 13.4        |
| 1751072     | 12.62       | 0.05        | 127         | 24.4        | <1          | 10.8        |
| 1751073     | 22.85       | 0.07        | 68.15       | 24.7        | <1          | 3.1         |
| 1751074     | 7.25        | 0.06        | 68.12       | 24.4        | <1          | 2.8         |
| 1751075     | 5.73        | 0.06        | 110         | 29.8        | <1          | 2.6         |
| 1751076     | 6.65        | 0.03        | 68.26       | 13.2        | <1          | 10.9        |
| 1751077     | 1.75        | <0.02       | 65.08       | 8.8         | <1          | 8.8         |
| 1751078     | 6.15        | <0.02       | 115         | 15.0        | <1          | 13.6        |
| 1751079     | 46.46       | 0.09        | 36.26       | 96.2        | <1          | 1.7         |
| 1751080     | -           | -           | -           | -           | -           | -           |
| 1751081     | 62.14       | 0.03        | 25.49       | 31.7        | <1          | 4.8         |
| 1751082     | 0.65        | 0.03        | 1.32        | 1.4         | <1          | 1.6         |
| 1751083     | 25.99       | <0.02       | 44.61       | 16.1        | <1          | 12.1        |
| 1751084     | 34.07       | 0.02        | 95.71       | 5.4         | <1          | 14.2        |

- not analysed | -- element not determined | I.S. insufficient sample | L.N.R. listed not received



Order Number PANCON\_RESOURCES  
 Project The Brewer Gold Project  
 Submission Number \*SD\* Pancon/ Brewer Gold B21C-  
 009/ 111 Core (57-111)  
 Number of Samples 55

**ANALYSIS REPORT BBM21-09950**

| Element        | @Bi         | @Cd         | @Ce         | @Co         | @Cs         | @Ga         |
|----------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Method         | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 |
| Lower Limit    | 0.04        | 0.02        | 0.05        | 0.1         | 1           | 0.1         |
| Upper Limit    | 10,000      | 10,000      | 1,000       | 10,000      | 1,000       | 1,000       |
| Unit           | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   |
| 1751085        | 191         | 0.05        | 93.49       | 32.8        | <1          | 18.4        |
| 1751086        | 25.40       | 0.03        | 1.52        | 1.2         | <1          | 1.5         |
| 1751087        | 217         | 0.03        | 41.89       | 23.4        | <1          | 4.5         |
| 1751088        | 260         | 0.06        | 36.90       | 43.2        | <1          | 23.6        |
| 1751089        | 91.53       | 0.08        | 96.83       | 76.8        | <1          | 17.0        |
| 1751090        | -           | -           | -           | -           | -           | -           |
| 1751091        | 42.05       | 0.02        | 96.61       | 33.3        | <1          | 6.2         |
| 1751092        | 36.80       | 0.05        | 33.57       | 26.4        | <1          | 15.4        |
| 1751093        | 4.03        | <0.02       | 27.14       | 16.4        | <1          | 6.2         |
| 1751094        | 1.06        | <0.02       | 53.59       | 3.5         | <1          | 8.6         |
| 1751095        | 14.04       | 0.03        | 39.11       | 14.9        | <1          | 6.9         |
| 1751096        | 4.21        | 0.04        | 4.39        | 10.2        | <1          | 1.9         |
| 1751097        | 1.66        | <0.02       | 23.87       | 8.1         | <1          | 5.9         |
| 1751098        | 1.59        | 0.02        | 40.85       | 13.7        | <1          | 10.5        |
| 1751099        | 3.21        | 0.03        | 111         | 16.4        | <1          | 11.6        |
| 1751100        | -           | -           | -           | -           | -           | -           |
| 1751101        | 2.25        | 0.03        | 19.64       | 21.0        | <1          | 16.9        |
| 1751102        | 7.66        | 0.04        | 80.20       | 18.8        | 2           | 21.6        |
| 1751103        | 7.37        | <0.02       | 81.01       | 19.9        | 2           | 21.9        |
| 1751104        | 6.50        | <0.02       | 43.01       | 25.4        | 3           | 27.1        |
| 1751105        | 3.31        | <0.02       | 37.76       | 11.4        | 3           | 17.4        |
| 1751106        | 7.29        | 0.02        | 82.49       | 14.1        | 3           | 18.2        |
| 1751107        | 8.04        | 0.05        | 33.93       | 10.0        | 2           | 8.8         |
| 1751108        | 2.62        | 0.02        | 45.09       | 3.2         | 1           | 12.1        |
| 1751109        | 2.73        | 0.03        | 28.81       | 3.5         | <1          | 17.0        |
| 1751110        | -           | -           | -           | -           | -           | -           |
| 1751111        | 11.90       | 0.07        | 97.03       | 18.1        | 2           | 24.9        |
| *Dup 1751095   | 11.55       | 0.03        | 34.18       | 14.7        | <1          | 6.5         |
| *Std OREAS 905 | 5.78        | 0.71        | 90.79       | 14.8        | 7           | 25.7        |

- not analysed | -- element not determined | I.S. insufficient sample | L.N.R. listed not received



Order Number PANCON\_RESOURCES  
 Project The Brewer Gold Project  
 Submission Number \*SD\* Pancon/ Brewer Gold B21C-  
 009/ 111 Core (57-111)  
 Number of Samples 55

## ANALYSIS REPORT BBM21-09950

| Element         | @Bi         | @Cd         | @Ce         | @Co         | @Cs         | @Ga         |
|-----------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Method          | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 |
| Lower Limit     | 0.04        | 0.02        | 0.05        | 0.1         | 1           | 0.1         |
| Upper Limit     | 10,000      | 10,000      | 1,000       | 10,000      | 1,000       | 1,000       |
| Unit            | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   |
| *Blk BLANK      | <0.04       | <0.02       | 0.11        | <0.1        | <1          | <0.1        |
| *Blk BLANK      | <0.04       | <0.02       | 0.12        | <0.1        | <1          | <0.1        |
| *Std OREAS 601b | 18.07       | 1.96        | 73.96       | 3.0         | 5           | 23.4        |
| *Std OREAS 905  | 5.78        | 0.34        | 93.34       | 15.4        | 8           | 26.6        |
| *Std OREAS 601b | 16.74       | 2.06        | 70.99       | 3.0         | 5           | 23.5        |
| *Blk BLANK      | <0.04       | <0.02       | 0.07        | <0.1        | <1          | <0.1        |
| *Rep 1751109    | 2.78        | <0.02       | 27.84       | 3.5         | <1          | 15.9        |

| Element     | @Hf         | @In         | @La         | @Lu         | @Mo         | @Nb         |
|-------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Method      | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 |
| Lower Limit | 0.02        | 0.02        | 0.1         | 0.01        | 0.05        | 0.1         |
| Upper Limit | 500         | 500         | 10,000      | 1,000       | 10,000      | 1,000       |
| Unit        | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   |
| 1751057     | 2.63        | <0.02       | 31.5        | 0.14        | 31.59       | 3.1         |
| 1751058     | 2.86        | <0.02       | 26.5        | 0.15        | 26.32       | 3.2         |
| 1751059     | 2.58        | <0.02       | 19.0        | 0.12        | 31.22       | 2.6         |
| 1751060     | -           | -           | -           | -           | -           | -           |
| 1751061     | 1.86        | <0.02       | 33.3        | 0.09        | 9.53        | 2.2         |
| 1751062     | 1.78        | <0.02       | 33.4        | 0.08        | 8.84        | 2.3         |
| 1751063     | 2.39        | <0.02       | 27.8        | 0.11        | 9.22        | 2.5         |
| 1751064     | 2.48        | <0.02       | 42.8        | 0.13        | 16.57       | 2.2         |
| 1751065     | 2.36        | <0.02       | 38.3        | 0.12        | 10.05       | 3.1         |
| 1751066     | 2.30        | <0.02       | 30.1        | 0.09        | 9.06        | 2.6         |
| 1751067     | 2.66        | 0.02        | 60.8        | 0.13        | 47.31       | 2.2         |
| 1751068     | 3.56        | <0.02       | 62.9        | 0.18        | 9.81        | 2.9         |
| 1751069     | 3.33        | 0.02        | 34.0        | 0.17        | 10.26       | 2.0         |
| 1751070     | -           | -           | -           | -           | -           | -           |
| 1751071     | 2.43        | 0.02        | 33.0        | 0.13        | 8.32        | 1.6         |

- not analysed | -- element not determined | I.S. insufficient sample | L.N.R. listed not received



Order Number PANCON\_RESOURCES  
 Project The Brewer Gold Project  
 Submission Number \*SD\* Pancon/ Brewer Gold B21C-  
 009/ 111 Core (57-111)  
 Number of Samples 55

## ANALYSIS REPORT BBM21-09950

| Element     | @Hf         | @In         | @La         | @Lu         | @Mo         | @Nb         |
|-------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Method      | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 |
| Lower Limit | 0.02        | 0.02        | 0.1         | 0.01        | 0.05        | 0.1         |
| Upper Limit | 500         | 500         | 10,000      | 1,000       | 10,000      | 1,000       |
| Unit        | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   |
| 1751072     | 2.50        | 0.02        | 50.9        | 0.13        | 6.28        | 1.6         |
| 1751073     | 2.97        | 0.05        | 37.8        | 0.18        | 11.58       | 1.5         |
| 1751074     | 1.99        | 0.02        | 38.2        | 0.12        | 9.31        | 0.9         |
| 1751075     | 1.92        | 0.03        | 60.0        | 0.11        | 12.40       | 1.0         |
| 1751076     | 1.86        | <0.02       | 36.0        | 0.10        | 2.88        | 1.8         |
| 1751077     | 2.27        | <0.02       | 34.7        | 0.11        | 2.72        | 2.0         |
| 1751078     | 3.47        | <0.02       | 60.1        | 0.18        | 5.30        | 3.0         |
| 1751079     | 3.08        | 0.04        | 17.5        | 0.14        | 10.18       | 1.6         |
| 1751080     | -           | -           | -           | -           | -           | -           |
| 1751081     | 2.72        | <0.02       | 12.8        | 0.14        | 5.54        | 1.8         |
| 1751082     | 0.23        | <0.02       | 0.7         | 0.02        | 1.09        | 0.2         |
| 1751083     | 3.29        | <0.02       | 20.8        | 0.15        | 4.76        | 4.3         |
| 1751084     | 1.84        | <0.02       | 48.4        | 0.08        | 2.41        | 1.7         |
| 1751085     | 3.57        | 0.05        | 45.6        | 0.18        | 20.29       | 3.4         |
| 1751086     | 0.47        | <0.02       | 0.8         | 0.02        | 3.58        | 0.3         |
| 1751087     | 2.87        | 0.04        | 20.7        | 0.15        | 5.88        | 2.0         |
| 1751088     | 2.19        | 0.05        | 18.0        | 0.11        | 4.95        | 1.9         |
| 1751089     | 2.58        | 0.04        | 46.8        | 0.14        | 8.11        | 1.3         |
| 1751090     | -           | -           | -           | -           | -           | -           |
| 1751091     | 2.58        | <0.02       | 47.5        | 0.14        | 5.81        | 1.7         |
| 1751092     | 2.88        | 0.03        | 15.5        | 0.14        | 5.92        | 2.2         |
| 1751093     | 2.76        | <0.02       | 13.6        | 0.15        | 4.90        | 1.5         |
| 1751094     | 2.57        | <0.02       | 24.7        | 0.14        | 2.00        | 2.1         |
| 1751095     | 2.47        | 0.03        | 18.7        | 0.14        | 5.38        | 1.6         |
| 1751096     | 2.34        | 0.03        | 2.0         | 0.15        | 3.92        | 1.3         |
| 1751097     | 2.50        | 0.05        | 11.2        | 0.16        | 2.64        | 1.7         |
| 1751098     | 2.86        | 0.05        | 18.5        | 0.15        | 2.93        | 2.2         |
| 1751099     | 2.74        | 0.03        | 51.9        | 0.15        | 2.60        | 1.2         |
| 1751100     | -           | -           | -           | -           | -           | -           |

- not analysed | -- element not determined | I.S. insufficient sample | L.N.R. listed not received





Order Number PANCON\_RESOURCES  
 Project The Brewer Gold Project  
 Submission Number \*SD\* Pancon/ Brewer Gold B21C-  
 009/ 111 Core (57-111)  
 Number of Samples 55

## ANALYSIS REPORT BBM21-09950

| Element         | @Hf         | @In         | @La         | @Lu         | @Mo         | @Nb         |
|-----------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Method          | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 |
| Lower Limit     | 0.02        | 0.02        | 0.1         | 0.01        | 0.05        | 0.1         |
| Upper Limit     | 500         | 500         | 10,000      | 1,000       | 10,000      | 1,000       |
| Unit            | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   |
| 1751101         | 2.27        | 0.03        | 9.5         | 0.14        | 2.56        | 1.1         |
| 1751102         | 1.82        | 0.14        | 38.6        | 0.11        | 3.59        | 1.0         |
| 1751103         | 2.55        | 0.16        | 36.9        | 0.16        | 4.23        | 1.3         |
| 1751104         | 2.94        | 0.20        | 18.2        | 0.16        | 3.85        | 1.7         |
| 1751105         | 2.06        | 0.15        | 18.0        | 0.12        | 2.97        | 1.4         |
| 1751106         | 1.86        | 0.15        | 33.1        | 0.11        | 3.20        | 1.2         |
| 1751107         | 2.13        | 0.07        | 14.3        | 0.14        | 7.04        | 1.2         |
| 1751108         | 2.59        | 0.06        | 20.8        | 0.15        | 12.38       | 1.7         |
| 1751109         | 2.56        | 0.05        | 13.9        | 0.14        | 12.00       | 2.4         |
| 1751110         | -           | -           | -           | -           | -           | -           |
| 1751111         | 2.32        | 0.07        | 47.2        | 0.14        | 4.75        | 1.1         |
| *Dup 1751095    | 2.57        | 0.03        | 16.1        | 0.15        | 5.10        | 1.8         |
| *Std OREAS 905  | 7.15        | 0.71        | 46.6        | 0.10        | 3.44        | 18.7        |
| *Blk BLANK      | <0.02       | <0.02       | <0.1        | <0.01       | 0.10        | <0.1        |
| *Blk BLANK      | <0.02       | <0.02       | <0.1        | <0.01       | <0.05       | <0.1        |
| *Std OREAS 601b | 5.38        | 0.46        | 33.4        | 0.07        | 5.09        | 15.1        |
| *Std OREAS 905  | 7.29        | 0.71        | 43.9        | 0.10        | 3.56        | 18.3        |
| *Std OREAS 601b | 5.23        | 0.50        | 34.0        | 0.08        | 5.11        | 15.8        |
| *Blk BLANK      | <0.02       | <0.02       | 0.2         | <0.01       | 0.06        | <0.1        |
| *Rep 1751109    | 2.40        | 0.05        | 13.5        | 0.13        | 11.92       | 1.9         |

| Element     | @Pb         | @Rb         | @Sb         | @Sc         | @Se         | @Sn         |
|-------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Method      | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 |
| Lower Limit | 0.5         | 0.2         | 0.05        | 0.5         | 2           | 0.3         |
| Upper Limit | 10,000      | 10,000      | 10,000      | 10,000      | 1,000       | 1,000       |
| Unit        | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   |
| 1751057     | 73.6        | 0.8         | 0.47        | 2.9         | 12          | 5.7         |
| 1751058     | 124         | 0.9         | 0.81        | 3.3         | 13          | 6.8         |

- not analysed | -- element not determined | I.S. insufficient sample | L.N.R. listed not received



Order Number PANCON\_RESOURCES  
 Project The Brewer Gold Project  
 Submission Number \*SD\* Pancon/ Brewer Gold B21C-  
 009/ 111 Core (57-111)  
 Number of Samples 55

## ANALYSIS REPORT BBM21-09950

| Element     | @Pb         | @Rb         | @Sb         | @Sc         | @Se         | @Sn         |
|-------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Method      | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 |
| Lower Limit | 0.5         | 0.2         | 0.05        | 0.5         | 2           | 0.3         |
| Upper Limit | 10,000      | 10,000      | 10,000      | 10,000      | 1,000       | 1,000       |
| Unit        | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   |
| 1751059     | 133         | 0.7         | 0.38        | 2.9         | 9           | 3.9         |
| 1751060     | -           | -           | -           | -           | -           | -           |
| 1751061     | 179         | 1.3         | 0.24        | 2.2         | <2          | 3.2         |
| 1751062     | 122         | 0.7         | 0.35        | 1.7         | 3           | 3.4         |
| 1751063     | 107         | 1.2         | 0.30        | 2.6         | 5           | 4.1         |
| 1751064     | 174         | 0.8         | 0.22        | 3.2         | 6           | 3.6         |
| 1751065     | 165         | 1.4         | 0.33        | 2.9         | 5           | 4.7         |
| 1751066     | 253         | 0.6         | 0.36        | 1.6         | 4           | 4.5         |
| 1751067     | 317         | 0.7         | 0.50        | 2.9         | 13          | 4.9         |
| 1751068     | 171         | 0.4         | 0.69        | 3.7         | 13          | 4.2         |
| 1751069     | 135         | 0.7         | 1.90        | 3.4         | 15          | 4.0         |
| 1751070     | -           | -           | -           | -           | -           | -           |
| 1751071     | 141         | 0.7         | 0.51        | 3.7         | 17          | 3.9         |
| 1751072     | 163         | 0.3         | 0.56        | 3.3         | 15          | 3.9         |
| 1751073     | 104         | 0.4         | 0.47        | 3.3         | 27          | 3.2         |
| 1751074     | 64.6        | 0.2         | 0.58        | 2.3         | 24          | 1.8         |
| 1751075     | 113         | <0.2        | 0.81        | 2.0         | 33          | 1.9         |
| 1751076     | 88.4        | 0.4         | 0.33        | 2.3         | 7           | 3.3         |
| 1751077     | 63.5        | 0.3         | 0.37        | 2.4         | 4           | 4.0         |
| 1751078     | 170         | 0.5         | 0.51        | 3.9         | 8           | 6.5         |
| 1751079     | 54.2        | 0.2         | 1.94        | 2.5         | 62          | 5.6         |
| 1751080     | -           | -           | -           | -           | -           | -           |
| 1751081     | 36.3        | 0.3         | 0.66        | 2.9         | 22          | 4.9         |
| 1751082     | 1.9         | <0.2        | 0.17        | <0.5        | <2          | 0.4         |
| 1751083     | 76.5        | 0.5         | 0.77        | 3.3         | 9           | 5.4         |
| 1751084     | 110         | 0.4         | 0.46        | 2.2         | 6           | 3.7         |
| 1751085     | 147         | 0.4         | 1.22        | 3.9         | 44          | 9.4         |
| 1751086     | 1.8         | <0.2        | 0.33        | 0.5         | 5           | 1.0         |
| 1751087     | 29.5        | 0.3         | 1.15        | 3.1         | 42          | 5.6         |

- not analysed | -- element not determined | I.S. insufficient sample | L.N.R. listed not received



Order Number PANCON\_RESOURCES  
 Project The Brewer Gold Project  
 Submission Number \*SD\* Pancon/ Brewer Gold B21C-  
 009/ 111 Core (57-111)  
 Number of Samples 55

## ANALYSIS REPORT BBM21-09950

| Element         | @Pb         | @Rb         | @Sb         | @Sc         | @Se         | @Sn         |
|-----------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Method          | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 |
| Lower Limit     | 0.5         | 0.2         | 0.05        | 0.5         | 2           | 0.3         |
| Upper Limit     | 10,000      | 10,000      | 10,000      | 10,000      | 1,000       | 1,000       |
| Unit            | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   |
| 1751088         | 85.6        | 0.4         | 1.71        | 2.6         | 48          | 21.6        |
| 1751089         | 139         | 0.7         | 0.99        | 2.8         | 30          | 18.2        |
| 1751090         | -           | -           | -           | -           | -           | -           |
| 1751091         | 83.3        | 0.3         | 0.45        | 3.2         | 15          | 5.6         |
| 1751092         | 119         | 0.8         | 0.66        | 3.4         | 20          | 5.9         |
| 1751093         | 36.4        | 0.9         | 0.46        | 3.8         | 13          | 3.4         |
| 1751094         | 57.2        | 1.7         | 0.32        | 3.7         | 2           | 3.8         |
| 1751095         | 80.4        | 2.0         | 0.18        | 3.2         | 8           | 3.9         |
| 1751096         | 12.1        | 3.4         | 0.16        | 3.6         | 13          | 2.1         |
| 1751097         | 24.9        | 4.6         | 0.27        | 3.9         | 8           | 3.4         |
| 1751098         | 39.6        | 4.5         | 0.30        | 4.5         | 5           | 3.7         |
| 1751099         | 91.0        | 2.2         | 0.32        | 2.8         | 14          | 2.3         |
| 1751100         | -           | -           | -           | -           | -           | -           |
| 1751101         | 17.5        | 3.1         | 0.30        | 3.0         | 20          | 2.0         |
| 1751102         | 114         | 23.1        | 0.26        | 4.7         | 17          | 7.8         |
| 1751103         | 165         | 25.9        | 0.32        | 5.8         | 19          | 8.3         |
| 1751104         | 184         | 39.9        | 0.32        | 7.2         | 19          | 9.5         |
| 1751105         | 129         | 36.1        | 0.19        | 6.2         | 8           | 5.6         |
| 1751106         | 306         | 45.0        | 0.36        | 6.1         | 19          | 6.3         |
| 1751107         | 271         | 24.1        | 0.31        | 4.8         | 13          | 4.0         |
| 1751108         | 285         | 17.0        | 0.29        | 5.5         | 5           | 4.0         |
| 1751109         | 335         | 15.5        | 0.32        | 4.8         | 4           | 4.2         |
| 1751110         | -           | -           | -           | -           | -           | -           |
| 1751111         | 373         | 26.1        | 0.30        | 5.6         | 15          | 5.2         |
| *Dup 1751095    | 69.9        | 1.6         | 0.21        | 3.4         | 7           | 3.8         |
| *Std OREAS 905  | 29.1        | 138         | 2.02        | 5.3         | 3           | 4.3         |
| *Blk BLANK      | <0.5        | <0.2        | <0.05       | <0.5        | <2          | <0.3        |
| *Blk BLANK      | <0.5        | <0.2        | <0.05       | <0.5        | <2          | <0.3        |
| *Std OREAS 601b | 306         | 95.0        | 22.31       | 4.4         | 9           | 3.1         |

- not analysed | -- element not determined | I.S. insufficient sample | L.N.R. listed not received



Order Number PANCON\_RESOURCES  
 Project The Brewer Gold Project  
 Submission Number \*SD\* Pancon/ Brewer Gold B21C-  
 009/ 111 Core (57-111)  
 Number of Samples 55

## ANALYSIS REPORT BBM21-09950

| Element         | @Pb         | @Rb         | @Sb         | @Sc         | @Se         | @Sn         |
|-----------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Method          | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 |
| Lower Limit     | 0.5         | 0.2         | 0.05        | 0.5         | 2           | 0.3         |
| Upper Limit     | 10,000      | 10,000      | 10,000      | 10,000      | 1,000       | 1,000       |
| Unit            | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   |
| *Std OREAS 905  | 28.2        | 147         | 2.05        | 5.2         | 3           | 4.3         |
| *Std OREAS 601b | 301         | 97.4        | 24.66       | 3.9         | 10          | 3.5         |
| *Blk BLANK      | <0.5        | <0.2        | <0.05       | <0.5        | <2          | <0.3        |
| *Rep 1751109    | 331         | 14.9        | 0.29        | 4.6         | 4           | 3.8         |

| Element     | @Ta         | @Tb         | @Te         | @Th         | @Tl         | @U          |
|-------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Method      | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 |
| Lower Limit | 0.05        | 0.05        | 0.05        | 0.2         | 0.02        | 0.05        |
| Upper Limit | 10,000      | 10,000      | 1,000       | 10,000      | 10,000      | 10,000      |
| Unit        | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   |
| 1751057     | 0.23        | 0.28        | 2.99        | 10.0        | 0.03        | 1.03        |
| 1751058     | 0.37        | 0.28        | 4.59        | 10.3        | 0.03        | 1.04        |
| 1751059     | 0.36        | 0.24        | 2.46        | 7.9         | 0.03        | 0.96        |
| 1751060     | -           | -           | -           | -           | -           | -           |
| 1751061     | 0.51        | 0.27        | 0.35        | 11.5        | 0.06        | 0.82        |
| 1751062     | 0.53        | 0.26        | 0.91        | 8.2         | 0.04        | 1.03        |
| 1751063     | 0.49        | 0.29        | 1.26        | 8.5         | 0.06        | 1.17        |
| 1751064     | 0.37        | 0.35        | 2.02        | 14.3        | 0.05        | 1.34        |
| 1751065     | 0.75        | 0.35        | 2.40        | 10.5        | 0.09        | 1.31        |
| 1751066     | 0.31        | 0.28        | 1.90        | 9.4         | 0.05        | 1.32        |
| 1751067     | 0.34        | 0.49        | 5.65        | 15.8        | 0.06        | 1.60        |
| 1751068     | 0.22        | 0.48        | 5.66        | 13.9        | 0.02        | 1.96        |
| 1751069     | 0.19        | 0.33        | 20.57       | 10.1        | 0.05        | 1.58        |
| 1751070     | -           | -           | -           | -           | -           | -           |
| 1751071     | 0.18        | 0.39        | 5.77        | 9.3         | 0.02        | 1.11        |
| 1751072     | 0.13        | 0.42        | 6.81        | 13.5        | 0.06        | 1.20        |
| 1751073     | 0.07        | 0.24        | 7.88        | 10.4        | 0.15        | 1.28        |
| 1751074     | 0.13        | 0.24        | 6.00        | 11.0        | 0.22        | 0.97        |

- not analysed | -- element not determined | I.S. insufficient sample | L.N.R. listed not received



Order Number PANCON\_RESOURCES  
 Project The Brewer Gold Project  
 Submission Number \*SD\* Pancon/ Brewer Gold B21C-  
 009/ 111 Core (57-111)  
 Number of Samples 55

**ANALYSIS REPORT BBM21-09950**

| Element     | @Ta         | @Tb         | @Te         | @Th         | @Tl         | @U          |
|-------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Method      | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 |
| Lower Limit | 0.05        | 0.05        | 0.05        | 0.2         | 0.02        | 0.05        |
| Upper Limit | 10,000      | 10,000      | 1,000       | 10,000      | 10,000      | 10,000      |
| Unit        | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   |
| 1751075     | <0.05       | 0.27        | 6.64        | 16.7        | 0.16        | 0.80        |
| 1751076     | 0.17        | 0.29        | 2.22        | 8.9         | 0.03        | 1.01        |
| 1751077     | 0.15        | 0.23        | 1.60        | 9.0         | <0.02       | 1.10        |
| 1751078     | 0.21        | 0.29        | 2.04        | 16.3        | 0.04        | 1.43        |
| 1751079     | 0.09        | 0.14        | 39.07       | 6.8         | 0.24        | 1.10        |
| 1751080     | -           | -           | -           | -           | -           | -           |
| 1751081     | 0.09        | 0.11        | 7.22        | 4.7         | 0.06        | 0.97        |
| 1751082     | <0.05       | <0.05       | 0.38        | 0.3         | <0.02       | 0.10        |
| 1751083     | 0.47        | 0.15        | 2.97        | 7.8         | 0.04        | 1.09        |
| 1751084     | 0.17        | 0.19        | 2.01        | 14.6        | 0.03        | 0.68        |
| 1751085     | 0.39        | 0.24        | 9.53        | 14.3        | 0.05        | 1.35        |
| 1751086     | <0.05       | <0.05       | 2.51        | 0.3         | <0.02       | 0.16        |
| 1751087     | 0.10        | 0.11        | 27.16       | 6.6         | 0.05        | 0.92        |
| 1751088     | 0.28        | 0.12        | 16.89       | 6.1         | 0.10        | 0.84        |
| 1751089     | 0.12        | 0.24        | 11.64       | 15.4        | 0.14        | 0.99        |
| 1751090     | -           | -           | -           | -           | -           | -           |
| 1751091     | 0.08        | 0.21        | 5.44        | 15.8        | 0.05        | 0.93        |
| 1751092     | 0.21        | 0.13        | 13.93       | 6.4         | 0.17        | 1.01        |
| 1751093     | 0.07        | 0.11        | 2.45        | 5.0         | 0.10        | 1.12        |
| 1751094     | 0.14        | 0.21        | 0.73        | 8.9         | 0.11        | 1.27        |
| 1751095     | 0.06        | 0.23        | 6.29        | 7.0         | 0.23        | 1.21        |
| 1751096     | 0.07        | 0.12        | 4.18        | 1.4         | 0.20        | 0.88        |
| 1751097     | 0.08        | 0.12        | 3.14        | 5.1         | 0.29        | 1.09        |
| 1751098     | 0.17        | 0.20        | 2.53        | 6.9         | 0.32        | 1.23        |
| 1751099     | 0.06        | 0.27        | 4.92        | 16.5        | 0.12        | 1.05        |
| 1751100     | -           | -           | -           | -           | -           | -           |
| 1751101     | 0.11        | 0.07        | 5.76        | 3.4         | 0.12        | 0.76        |
| 1751102     | 0.22        | 0.21        | 3.55        | 12.3        | 0.80        | 0.71        |
| 1751103     | 0.26        | 0.24        | 4.21        | 11.6        | 0.92        | 1.05        |

- not analysed | -- element not determined | I.S. insufficient sample | L.N.R. listed not received



Order Number PANCON\_RESOURCES  
 Project The Brewer Gold Project  
 Submission Number \*SD\* Pancon/ Brewer Gold B21C-  
 009/ 111 Core (57-111)  
 Number of Samples 55

**ANALYSIS REPORT BBM21-09950**

| Element<br>Method<br>Lower Limit<br>Upper Limit<br>Unit | @Ta<br>GE_IMS40Q12<br>0.05<br>10,000<br>ppm m / m | @Tb<br>GE_IMS40Q12<br>0.05<br>10,000<br>ppm m / m | @Te<br>GE_IMS40Q12<br>0.05<br>1,000<br>ppm m / m | @Th<br>GE_IMS40Q12<br>0.2<br>10,000<br>ppm m / m | @Tl<br>GE_IMS40Q12<br>0.02<br>10,000<br>ppm m / m | @U<br>GE_IMS40Q12<br>0.05<br>10,000<br>ppm m / m |
|---|---|---|--|--|---|--|
| 1751104   | 0.46  | 0.24  | 3.86   | 6.9  | 1.66  | 1.11   |
| 1751105   | 0.27  | 0.15  | 2.52   | 6.4  | 1.70  | 0.79   |
| 1751106   | 0.39  | 0.28  | 5.46   | 10.1   | 1.71  | 0.98   |
| 1751107   | 0.09  | 0.20  | 5.10   | 5.2  | 0.84  | 0.97   |
| 1751108   | 0.11  | 0.16  | 3.93   | 6.2  | 1.09  | 0.99   |
| 1751109   | 0.19  | 0.13  | 3.20   | 6.1  | 0.69  | 0.88   |
| 1751110   | -   | -   | -  | -  | -   | -  |
| 1751111   | 0.12  | 0.31  | 5.87   | 13.2   | 0.90  | 0.92   |
| *Dup 1751095  | 0.09  | 0.20  | 9.11   | 6.1  | 0.19  | 1.20   |
| *Std OREAS 905  | 1.41  | 0.82  | 0.08   | 14.5   | 0.77  | 5.20   |
| *Blk BLANK  | <0.05   | <0.05   | <0.05  | <0.2   | <0.02   | <0.05  |
| *Blk BLANK  | <0.05   | <0.05   | <0.05  | <0.2   | <0.02   | <0.05  |
| *Std OREAS 601b   | 1.17  | 0.58  | 11.33  | 11.5   | 1.46  | 4.42   |
| *Std OREAS 905  | 1.39  | 0.83  | 0.13   | 14.4   | 0.79  | 5.23   |
| *Std OREAS 601b   | 1.18  | 0.56  | 12.72  | 12.2   | 1.57  | 4.83   |
| *Blk BLANK  | <0.05   | <0.05   | <0.05  | <0.2   | <0.02   | <0.05  |
| *Rep 1751109  | 0.14  | 0.12  | 3.38   | 5.9  | 0.70  | 0.86   |

| Element<br>Method<br>Lower Limit<br>Upper Limit<br>Unit | @W<br>GE_IMS40Q12<br>0.1<br>10,000<br>ppm m / m | @Y<br>GE_IMS40Q12<br>0.1<br>10,000<br>ppm m / m | @Yb<br>GE_IMS40Q12<br>0.1<br>1,000<br>ppm m / m | Dy<br>GE_IMS40Q12<br>0.05<br>1,000<br>ppm m / m | Er<br>GE_IMS40Q12<br>0.05<br>1,000<br>ppm m / m | Eu<br>GE_IMS40Q12<br>0.05<br>500<br>ppm m / m |
|---|---|---|---|---|---|---|
| 1751057   | 2.5   | 3.4   | 0.7   | 0.91  | 0.43  | 0.81  |
| 1751058   | 1.5   | 4.1   | 0.8   | 1.01  | 0.51  | 0.78  |
| 1751059   | 1.0   | 3.1   | 0.6   | 0.83  | 0.39  | 0.61  |
| 1751060   | -   | -   | -   | -   | -   | -   |
| 1751061   | 0.7   | 2.7   | 0.5   | 0.85  | 0.31  | 0.91  |

- not analysed | -- element not determined | I.S. insufficient sample | L.N.R. listed not received



Order Number PANCON\_RESOURCES  
 Project The Brewer Gold Project  
 Submission Number \*SD\* Pancon/ Brewer Gold B21C-  
 009/ 111 Core (57-111)  
 Number of Samples 55

**ANALYSIS REPORT BBM21-09950**

| Element     | @W          | @Y          | @Yb         | Dy          | Er          | Eu          |
|-------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Method      | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 |
| Lower Limit | 0.1         | 0.1         | 0.1         | 0.05        | 0.05        | 0.05        |
| Upper Limit | 10,000      | 10,000      | 1,000       | 1,000       | 1,000       | 500         |
| Unit        | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   |
| 1751062     | 1.1         | 3.1         | 0.4         | 1.03        | 0.31        | 0.81        |
| 1751063     | 1.5         | 5.1         | 0.6         | 1.28        | 0.52        | 0.76        |
| 1751064     | 1.3         | 5.8         | 0.7         | 1.49        | 0.58        | 1.00        |
| 1751065     | 1.7         | 6.6         | 0.6         | 1.58        | 0.62        | 0.89        |
| 1751066     | 2.0         | 3.5         | 0.5         | 1.18        | 0.56        | 0.79        |
| 1751067     | 1.8         | 7.0         | 0.7         | 1.95        | 0.68        | 1.31        |
| 1751068     | 1.9         | 6.3         | 1.0         | 1.82        | 0.73        | 1.39        |
| 1751069     | 0.9         | 6.3         | 0.9         | 1.41        | 0.69        | 0.93        |
| 1751070     | -           | -           | -           | -           | -           | -           |
| 1751071     | 1.2         | 6.7         | 0.8         | 1.86        | 0.82        | 1.04        |
| 1751072     | 1.0         | 6.2         | 0.7         | 1.70        | 0.76        | 1.46        |
| 1751073     | 0.6         | 4.7         | 0.9         | 1.01        | 0.63        | 0.89        |
| 1751074     | 0.3         | 3.9         | 0.6         | 0.94        | 0.46        | 0.87        |
| 1751075     | 0.4         | 3.3         | 0.6         | 0.73        | 0.41        | 1.44        |
| 1751076     | 0.7         | 4.7         | 0.5         | 1.12        | 0.51        | 0.90        |
| 1751077     | 0.8         | 4.3         | 0.6         | 0.92        | 0.50        | 0.82        |
| 1751078     | 1.4         | 4.8         | 0.9         | 1.02        | 0.63        | 1.39        |
| 1751079     | 0.9         | 3.4         | 0.8         | 0.61        | 0.49        | 0.52        |
| 1751080     | -           | -           | -           | -           | -           | -           |
| 1751081     | 1.1         | 3.3         | 0.8         | 0.56        | 0.48        | 0.36        |
| 1751082     | 0.2         | 0.4         | <0.1        | 0.06        | <0.05       | <0.05       |
| 1751083     | 1.2         | 3.4         | 0.8         | 0.64        | 0.49        | 0.62        |
| 1751084     | 0.8         | 1.9         | 0.5         | 0.48        | 0.28        | 1.08        |
| 1751085     | 1.9         | 4.4         | 1.0         | 0.84        | 0.59        | 1.16        |
| 1751086     | 0.2         | 0.5         | 0.1         | 0.07        | 0.08        | <0.05       |
| 1751087     | 1.1         | 3.0         | 0.8         | 0.52        | 0.45        | 0.49        |
| 1751088     | 1.3         | 2.5         | 0.6         | 0.47        | 0.37        | 0.48        |
| 1751089     | 1.0         | 3.2         | 0.7         | 0.72        | 0.44        | 1.24        |
| 1751090     | -           | -           | -           | -           | -           | -           |

- not analysed | -- element not determined | I.S. insufficient sample | L.N.R. listed not received



Order Number PANCON\_RESOURCES  
 Project The Brewer Gold Project  
 Submission Number \*SD\* Pancon/ Brewer Gold B21C-  
 009/ 111 Core (57-111)  
 Number of Samples 55

## ANALYSIS REPORT BBM21-09950

| Element         | @W          | @Y          | @Yb         | Dy          | Er          | Eu          |
|-----------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Method          | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 |
| Lower Limit     | 0.1         | 0.1         | 0.1         | 0.05        | 0.05        | 0.05        |
| Upper Limit     | 10,000      | 10,000      | 1,000       | 1,000       | 1,000       | 500         |
| Unit            | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   |
| 1751091         | 1.3         | 3.4         | 0.7         | 0.66        | 0.46        | 1.22        |
| 1751092         | 1.6         | 3.1         | 0.8         | 0.58        | 0.45        | 0.53        |
| 1751093         | 1.4         | 3.6         | 0.8         | 0.58        | 0.51        | 0.38        |
| 1751094         | 0.9         | 3.5         | 0.7         | 0.88        | 0.45        | 0.79        |
| 1751095         | 1.3         | 4.3         | 0.8         | 1.04        | 0.51        | 0.65        |
| 1751096         | 1.6         | 5.1         | 0.9         | 0.80        | 0.61        | 0.12        |
| 1751097         | 1.3         | 3.9         | 0.8         | 0.63        | 0.53        | 0.35        |
| 1751098         | 1.5         | 3.9         | 0.8         | 0.87        | 0.49        | 0.60        |
| 1751099         | 0.6         | 3.9         | 0.8         | 0.83        | 0.54        | 1.46        |
| 1751100         | -           | -           | -           | -           | -           | -           |
| 1751101         | 0.5         | 3.2         | 0.8         | 0.43        | 0.44        | 0.28        |
| 1751102         | 0.4         | 2.9         | 0.6         | 0.61        | 0.39        | 1.14        |
| 1751103         | 0.5         | 4.1         | 0.9         | 0.84        | 0.56        | 1.26        |
| 1751104         | 0.6         | 5.6         | 0.9         | 1.08        | 0.65        | 0.84        |
| 1751105         | 0.5         | 3.6         | 0.6         | 0.69        | 0.43        | 0.55        |
| 1751106         | 0.4         | 3.4         | 0.6         | 0.96        | 0.40        | 1.35        |
| 1751107         | 0.7         | 4.5         | 0.7         | 0.89        | 0.53        | 0.65        |
| 1751108         | 1.5         | 3.6         | 0.8         | 0.65        | 0.50        | 0.65        |
| 1751109         | 1.8         | 3.8         | 0.8         | 0.63        | 0.51        | 0.48        |
| 1751110         | -           | -           | -           | -           | -           | -           |
| 1751111         | 0.6         | 5.0         | 0.8         | 1.08        | 0.58        | 1.20        |
| *Dup 1751095    | 1.3         | 4.4         | 0.8         | 0.95        | 0.51        | 0.54        |
| *Std OREAS 905  | 2.5         | 16.6        | 0.7         | 3.69        | 1.13        | 1.40        |
| *Blk BLANK      | <0.1        | <0.1        | <0.1        | <0.05       | <0.05       | <0.05       |
| *Blk BLANK      | <0.1        | <0.1        | <0.1        | <0.05       | <0.05       | <0.05       |
| *Std OREAS 601b | 6.2         | 11.7        | 0.5         | 2.75        | 0.91        | 1.02        |
| *Std OREAS 905  | 2.8         | 17.0        | 0.7         | 3.81        | 1.15        | 1.43        |
| *Std OREAS 601b | 6.4         | 11.7        | 0.5         | 2.57        | 0.85        | 0.97        |
| *Blk BLANK      | <0.1        | <0.1        | <0.1        | <0.05       | <0.05       | <0.05       |

- not analysed | -- element not determined | I.S. insufficient sample | L.N.R. listed not received





Order Number PANCON\_RESOURCES  
 Project The Brewer Gold Project  
 Submission Number \*SD\* Pancon/ Brewer Gold B21C-  
 009/ 111 Core (57-111)  
 Number of Samples 55

**ANALYSIS REPORT BBM21-09950**

| Element      | @W          | @Y          | @Yb         | Dy          | Er          | Eu          |
|--------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Method       | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 |
| Lower Limit  | 0.1         | 0.1         | 0.1         | 0.05        | 0.05        | 0.05        |
| Upper Limit  | 10,000      | 10,000      | 1,000       | 1,000       | 1,000       | 500         |
| Unit         | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   |
| *Rep 1751109 | 1.6         | 3.6         | 0.7         | 0.60        | 0.44        | 0.48        |

| Element     | Gd          | Ho          | Nd          | Pr          | Sm          | Tm          |
|-------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Method      | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 |
| Lower Limit | 0.1         | 0.05        | 0.1         | 0.05        | 0.1         | 0.05        |
| Upper Limit | 1,000       | 500         | 1,000       | 1,000       | 1,000       | 500         |
| Unit        | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   |
| 1751057     | 2.4         | 0.14        | 21.1        | 6.62        | 3.3         | 0.09        |
| 1751058     | 2.5         | 0.16        | 18.2        | 5.71        | 3.1         | 0.10        |
| 1751059     | 2.0         | 0.13        | 13.5        | 4.06        | 2.3         | 0.07        |
| 1751061     | 2.5         | 0.12        | 23.5        | 7.16        | 3.8         | 0.06        |
| 1751062     | 2.3         | 0.14        | 22.3        | 6.91        | 3.4         | 0.05        |
| 1751063     | 2.3         | 0.22        | 20.7        | 6.26        | 3.3         | 0.07        |
| 1751064     | 3.0         | 0.25        | 30.8        | 9.35        | 4.4         | 0.09        |
| 1751065     | 2.6         | 0.27        | 25.5        | 8.07        | 3.7         | 0.09        |
| 1751066     | 2.6         | 0.20        | 28.9        | 8.56        | 4.0         | 0.07        |
| 1751067     | 3.9         | 0.31        | 40.2        | 12.33       | 5.6         | 0.09        |
| 1751068     | 4.3         | 0.29        | 45.1        | 13.60       | 6.8         | 0.12        |
| 1751069     | 2.7         | 0.25        | 23.1        | 7.02        | 3.6         | 0.12        |
| 1751071     | 3.2         | 0.29        | 24.1        | 7.22        | 3.9         | 0.11        |
| 1751072     | 4.1         | 0.26        | 40.0        | 11.81       | 6.3         | 0.10        |
| 1751073     | 2.5         | 0.19        | 25.5        | 7.59        | 3.9         | 0.12        |
| 1751074     | 2.4         | 0.17        | 24.6        | 7.50        | 3.9         | 0.08        |
| 1751075     | 3.4         | 0.13        | 42.0        | 12.38       | 6.6         | 0.07        |
| 1751076     | 2.6         | 0.20        | 25.4        | 7.71        | 4.0         | 0.08        |
| 1751077     | 2.2         | 0.18        | 23.9        | 7.31        | 3.6         | 0.08        |
| 1751078     | 3.4         | 0.20        | 41.6        | 12.37       | 6.3         | 0.12        |
| 1751079     | 1.4         | 0.14        | 13.8        | 4.24        | 2.2         | 0.09        |

- not analysed | -- element not determined | I.S. insufficient sample | L.N.R. listed not received



Order Number PANCON\_RESOURCES  
 Project The Brewer Gold Project  
 Submission Number \*SD\* Pancon/ Brewer Gold B21C-  
 009/ 111 Core (57-111)  
 Number of Samples 55

## ANALYSIS REPORT BBM21-09950

| Element      | Gd          | Ho          | Nd          | Pr          | Sm          | Tm          |
|--------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Method       | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 |
| Lower Limit  | 0.1         | 0.05        | 0.1         | 0.05        | 0.1         | 0.05        |
| Upper Limit  | 1,000       | 500         | 1,000       | 1,000       | 1,000       | 500         |
| Unit         | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   |
| 1751081      | 1.0         | 0.13        | 9.6         | 2.99        | 1.6         | 0.10        |
| 1751082      | <0.1        | <0.05       | 0.6         | 0.17        | 0.1         | <0.05       |
| 1751083      | 1.7         | 0.14        | 17.2        | 5.02        | 2.7         | 0.10        |
| 1751084      | 2.5         | 0.09        | 33.3        | 10.20       | 5.0         | 0.05        |
| 1751085      | 2.9         | 0.18        | 33.3        | 10.08       | 5.3         | 0.12        |
| 1751086      | <0.1        | <0.05       | 0.6         | 0.19        | <0.1        | <0.05       |
| 1751087      | 1.2         | 0.13        | 15.2        | 4.63        | 2.3         | 0.10        |
| 1751088      | 1.3         | 0.10        | 13.4        | 4.14        | 2.1         | 0.07        |
| 1751089      | 3.0         | 0.13        | 35.5        | 10.50       | 5.5         | 0.09        |
| 1751091      | 2.8         | 0.14        | 36.4        | 10.54       | 5.7         | 0.09        |
| 1751092      | 1.3         | 0.13        | 13.1        | 3.83        | 2.1         | 0.09        |
| 1751093      | 1.0         | 0.14        | 10.5        | 3.13        | 1.6         | 0.10        |
| 1751094      | 2.2         | 0.16        | 20.5        | 6.17        | 3.3         | 0.09        |
| 1751095      | 1.8         | 0.19        | 15.1        | 4.54        | 2.6         | 0.09        |
| 1751096      | 0.6         | 0.19        | 2.1         | 0.58        | 0.4         | 0.11        |
| 1751097      | 1.0         | 0.15        | 9.7         | 2.83        | 1.6         | 0.10        |
| 1751098      | 1.8         | 0.16        | 16.5        | 4.83        | 2.7         | 0.10        |
| 1751099      | 3.5         | 0.16        | 42.6        | 12.37       | 6.7         | 0.10        |
| 1751101      | 0.7         | 0.12        | 7.6         | 2.22        | 1.2         | 0.09        |
| 1751102      | 2.6         | 0.12        | 30.9        | 9.27        | 5.2         | 0.08        |
| 1751103      | 3.0         | 0.18        | 32.1        | 9.31        | 5.3         | 0.11        |
| 1751104      | 2.2         | 0.22        | 17.9        | 5.06        | 3.3         | 0.11        |
| 1751105      | 1.4         | 0.15        | 13.9        | 4.26        | 2.2         | 0.08        |
| 1751106      | 3.1         | 0.16        | 40.0        | 10.91       | 6.0         | 0.07        |
| 1751107      | 1.8         | 0.17        | 15.0        | 4.21        | 2.4         | 0.10        |
| 1751108      | 1.7         | 0.15        | 18.3        | 5.41        | 2.8         | 0.09        |
| 1751109      | 1.1         | 0.16        | 11.2        | 3.37        | 1.7         | 0.09        |
| 1751111      | 3.3         | 0.20        | 35.2        | 10.64       | 4.7         | 0.10        |
| *Dup 1751095 | 1.6         | 0.18        | 12.8        | 3.79        | 2.2         | 0.10        |

- not analysed | -- element not determined | I.S. insufficient sample | L.N.R. listed not received



Order Number PANCON\_RESOURCES  
 Project The Brewer Gold Project  
 Submission Number \*SD\* Pancon/ Brewer Gold B21C-  
 009/ 111 Core (57-111)  
 Number of Samples 55

**ANALYSIS REPORT BBM21-09950**

| Element         | Gd          | Ho          | Nd          | Pr          | Sm          | Tm          |
|-----------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Method          | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 | GE_IMS40Q12 |
| Lower Limit     | 0.1         | 0.05        | 0.1         | 0.05        | 0.1         | 0.05        |
| Upper Limit     | 1,000       | 500         | 1,000       | 1,000       | 1,000       | 500         |
| Unit            | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   | ppm m / m   |
| *Std OREAS 905  | 5.9         | 0.57        | 39.6        | 10.75       | 7.7         | 0.13        |
| *Blk BLANK      | <0.1        | <0.05       | <0.1        | <0.05       | <0.1        | <0.05       |
| *Blk BLANK      | <0.1        | <0.05       | <0.1        | <0.05       | <0.1        | <0.05       |
| *Std OREAS 601b | 4.4         | 0.41        | 30.8        | 8.45        | 5.8         | 0.10        |
| *Std OREAS 905  | 6.0         | 0.57        | 40.8        | 10.94       | 7.8         | 0.14        |
| *Std OREAS 601b | 4.1         | 0.40        | 30.1        | 8.50        | 5.4         | 0.10        |
| *Blk BLANK      | <0.1        | <0.05       | 0.1         | <0.05       | <0.1        | <0.05       |
| *Rep 1751109    | 1.1         | 0.14        | 10.9        | 3.30        | 1.7         | 0.09        |

| Element     | @S        |
|-------------|-----------|
| Method      | GE_CSA06V |
| Lower Limit | 0.005     |
| Upper Limit | 30        |
| Unit        | %         |
| 1751068     | 5.269     |
| 1751069     | 5.790     |
| 1751071     | 7.146     |
| 1751072     | 6.458     |
| 1751073     | 8.200     |
| 1751074     | 8.126     |
| 1751075     | 10.223    |
| 1751079     | 15.867    |
| 1751089     | 7.055     |
| 1751101     | 7.458     |
| 1751102     | 6.378     |
| 1751103     | 6.715     |
| 1751104     | 6.966     |
| 1751106     | 5.518     |

- not analysed | -- element not determined | I.S. insufficient sample | L.N.R. listed not received



Order Number PANCON\_RESOURCES  
Project The Brewer Gold Project  
Submission Number \*SD\* Pancon/ Brewer Gold B21C-  
009/ 111 Core (57-111)  
Number of Samples 55

## ANALYSIS REPORT BBM21-09950

| Element        | @S        |
|----------------|-----------|
| Method         | GE_CSA06V |
| Lower Limit    | 0.005     |
| Upper Limit    | 30        |
| Unit           | %         |
| 1751111        | 5.829     |
| *Rep 1751071   | 7.089     |
| *Std OREAS 135 | 7.433     |
| *Blk BLANK     | 0.011     |

SGS Canada Minerals Burnaby conforms to the requirements of ISO/IEC17025 for specific tests as listed on their scope of accreditation found at <https://www.scc.ca/en/search/laboratories/sgs>  
Tests and Elements marked with an "@" symbol in the report denote ISO/IEC17025 accreditation.

- not analysed | -- element not determined | I.S. insufficient sample | L.N.R. listed not received